

The team at Treadwell is excited and proud to be releasing the latest version of the FRP Grating Product Guide to the market.

Treadwell's product range has expanded progressively since our last release of our FRP grating guide and now includes extensive offerings such as GratEX® moulded FRP Grating, MoultrEX® Moultruded FRP Grating and GridEX® FRP Pultruded Grating, Flooring and Stair Treads. These products are offered with an encompassing range of ancillary components and fastenings, as well as floor elevation and embedment products.

Our EX-Series® FRP grating is designed for use in a multitude of environments where the grating may be subjected to continuous spills, electrical dangers, fumes, splashes or submersions. In such demanding environments, FRP grating will out perform the standard traditional grating options. Our FRP grating is available in standard panels or can be customised to specification.

Now with warehouses and distribution centres throughout Australia and New Zealand. Treadwell is your one stop shop for FRP - we stock, we modify and we deliver to ensure that Treadwell is the name you can rely on.

#### **A BRIEF HISTORY**

Treadwell Group is one of the most established names in the supply of Access Systems throughout Australia.

Our centrally located Adelaide fabrication facility, coupled with our second to none distribution network across Australia and our commitment to quality and testing, allows our technical staff to provide engineering and design assistance for any project.

With a broad history of installation in a wide range of challenging applications, including industrial process plants, mining applications, marine and costal environments as well as public infrastructure, Treadwell has the experience to help you specify the right resin systems and products every time.

If you have any unique design problems, chances are we've encountered something similar before. Get in contact today - Freecall **1800 246 800**.









#### **Treadwell Group Pty Ltd**

Australia P 1800 246 800 sales@treadwellgroup.com.au treadwellgroup.com.au New Zealand
P 0800 244 600
sales@treadwellgroup.co.nz
treadwellgroup.co.nz





### **EX-Series**<sup>®</sup>

### Contents













- 04 Ex-Series® Grating Key Selection Considerations
- EX-Series® Resin Selection Guide 05

### **GratEX**°

- GratEX® Moulded Fibreglass Grating 06
- 07 GratEX® Square Mesh
- 11 GratEX® Heavy Duty Square Mesh
- GratEX® Mini Mesh 13
- GratEX® Micro Mesh 18
- GratEX® Rectangular Mesh 20
- 22 GratEX® Heavy Duty Rectangular Mesh
- GratEX® Solid Surface Mesh 24
- 28 GratEX® Heavy Duty Solid Surface Mesh
- GratEX® Stair Treads 30
- GratEX® Stair Tread Kits 32
- GratEX® Fastening Clips and Installation Methods 33
- 35 GratEX® Fixing Assembly Combinations
- GratEX® Closed Load Bar Charts 39

### MoultrEX<sup>®</sup>

- 44 MoultrEX® Moultruded Fibreglass Grating
- MoultrEX® Installation Methods and Accessories 46

### **GridEX**°

- GridEX® Pultruded Fibreglass Grating 48
- GridEX® I Type Grating 49
- GridEX® T Type Grating 53
- GridEX® Bar Type Grating 56
- GridEX® Stair Treads and Landings 58
- GridEX® Installation Methods and Accessories 59

### **EX-Series**°

- P-Series® Phenolic Grating 60
- Colour Palette 62
- 64 **Grating Grit Grades**
- HygiGR8® 65
- 67 **Conductive Grating**
- 68 Terminology
- 69 Installation Suggestions & Tools
- Drafting Information & Manufacturing Tolerances 70
- **Embedment Angle** 71
- StormChief® 72
- 74 Access Hatches, Handles and Hinge Systems
- 75 **Elevated Support Systems**
- Appendix 1: Load Data Tables 77
- 78 Appendix 2: Chemical Resistance Guide
- Appendix 3: GratEX® Ordering Codes 82
- Appendix 4: MoultrEX® Ordering Codes 83
- Appendix 5: GridEX® Ordering Codes 84
- 85 Appendix 6a: GratEX® Fasteners Ordering Information
- 86 Appendix 6b: MoultrEX® Fasteners Ordering Information
- Appendix 6c: GridEX® Fasteners Ordering Information 87

Disclaimer: The information contained in this Treadwell design guide herein supplied is as a service to our customers and is intended to be used only as a general guide. It is not a substitute for proven engineering practices and designs.


## **EX-Series® Grating Key Selection Considerations**

Treadwell EX-Series® Fibreglass Reinforced Plastic (FRP) grating products are recommended for areas where physical properties are paramount to design and longevity. Treadwell offers a very extensive range of FRP grating products which incorporates three main product systems. Of these three distinct product ranges, there are key differences which you as a user or specifier need to be aware of. The below information outlines for you the key differences and the ideal scenarios in which each of the different types of grating are to be utilised.

### **GratEX® Moulded FRP Grating**

The perfect solution for areas where excessive amounts of penetrations (i.e. for piping) call for traditional uni-directional spanning products which make it horrendously expensive and inconvenient.


Characteristic/Application	Rating
Bi-directional spanning ability	• • • •
Uni-directional spanning ability	• • • •
Chemical Resistance	• • • •
Impact Resistance	• • • •
Weight sasving vs. metallic grating	• • • •
Open Area (allowing for air flow & light penetration)	• • • •
Panel size availability	• • • •
Pipe penetations	• • • • •



#### MoultrEX® Moultruded FRP Grating

An excellent product choice for those applications where a medium between great product performance over time and great aesthetics are called for, i.e. jetties, marinas, boardwalks and more!

ı		
	Characteristic/Application	Rating
	Bi-directional spanning ability	• • • •
	Uni-directional spanning ability	• • • •
	Chemical Resistance	• • • •
	Impact Resistance	• • • •
	Weight savings vs. metallic grating	• • • •
	Open Area (allowing for air flow & light penetration)	• • •
	Panel size availability	• •
	Pipe penetrations	• • • • •



### **GridEX® Pultruded FRP Grating**


The ultimate choice for areas where extremely high loadings, or larger spans present a challenge. Such applications include wide walkways, or where equipment needs to be installed on top of grating.

Characteristic/Application	Rating
Bi-directional spanning ability	• •
Uni-directional spanning ability	• • • •
Chemical Resistance	• • • •
Impact Resistance	• • • • •
Weight savings vs. metallic grating	• • • •
Open Area (allowing for air flow & light penetration)	• • •
Panel size availability	• • •
Pipe penetrations	• • •



Legend	Description	Legend	Description	Legend	Description
E	Product is compliant to the Australian Disability Access Code AS 1428.	इंग्निएन स	Product conforms to Australian Standard AS 1657 – 2018.	28.5 kg/m²	Product weight per square metre.
	Product is pet friendly. Product is heel safe.	AUSTRALIAN STANDARD	Product conforms to Australian Standard AS 1657 – 2018, Clause 4.5.	P5	Product conforms to Australian Standard AS 4586 2013. P5 Slip Resistance

### **EX-Series® Resin Selection Guide**



When choosing a resin type for your application, we highly recommend you consult us to ensure that the correct resin is specified. Considerations such as corrosion, environment, temperature, fire resistance, smoke and smoke toxicity requirements must be taken into account, and will dictate which resin system should be utilised for optimum performance over time.

Below is an overview of the resin systems offered in the Access Systems Range.

### **Options Overview**

O-Series® is an architectural grade polyester resin system with an intermediate level of chemical resistance, and is a good choice for commercial or light industrial applications, especially where moisture is prevalent. O-Series® is often utilised for public infrastructure applications were it has been proven to outperform traditional timber decking products. This system is manufactured with fire retardant additives.

I-Series® is a premium isopthalic resin system. This system provides an intermediate level of chemical resistance and is the correct choice for areas subjected to splash and spill contact with harsh chemicals. This system is an excellent general-purpose resin and is a more favourably priced alternative to the vinyl ester system. This system has a flame spread of 25 (Approximately 15) or less.

V-Series® is a vinyl ester resin system that provides the highest chemical resistance offered in the industry and has been developed for use in environments where FRP products are subject to frequent and direct contact with the harshest of chemicals including a broad range of acids and caustics. This system has a flame spread of 25 (Approximately 15) or less.

P-Series® is a phenolic resin system that is designed specifically for use where fire resistance, low smoke and low toxic fumes are critical. P-Series® is typically used in offshore applications and confined spaces where such criteria are an absolute necessity. This system is tested in accordance to ASTM E-84. Various products also conforming to US Coast Guard Approvals, Level 2 and 3, are also offered by Treadwell. This particular resin system has a flame spread rating of 5 and a smoke density rating of 5.

### **EX-Series® Resin Systems Comparison Chart**

	Chemical Resistance	Fire Retardance	Low Smoke	Halogen Free	Temperature Performance
O-Series® Polyester	• • •	• • • •	_	_	• • •
I-Series® Isopthalic	• • • •	• • • • •	_	_	• • • •
V-Series® Vinylester	• • • •	• • • • •	_	_	••••
P-Series® Phenolic	• • • •	••••	• • • •	• • • •	• • • •

## **GratEX® Moulded Fibreglass Grating**

# What is GratEX<sup>®</sup> **Moulded Fibreglass Grating**

Treadwell's GratEX® moulded FRP grating is a high strength, single piece construction mesh panel product. Treadwell offers both standard panel sizes as well as the option of custom panels made to order from your drawings, or alternatively, drawings provided by Treadwell's drafting department.

Cost effective GratEX® panels allow for effective on-site fabrication/trimming whilst ensuring that wastage is minimised. Load bearing bars in both directions allow for use without continuous side support and so contribute to cost effectiveness. GratEX® offers all the benefits available with grating made from other materials plus a host of superior benefits unequalled by steel or other metal alternatives.



### **GratEX®** Features and Benefits vs. Traditional Alternatives

	GratEX®	Stainless Steel	Galvanised Steel	Aluminium	Polyurethane
Chemical Resistance	• • • •	• • • •	•	• • •	• • • •
Strength	• • • •	• • • • •	• • • •	• • • •	• • •
Lightweight	• • • • •	•	•	• • • •	• • •
Electrical Resistance	• • • •	•	•	•	• • • •

### **GratEX® Surface Options**

Anti-Slip Surface (Standard). This surface is most Concave Surface. This is preferred for environments Plain Surface. This is a stock option that is widely hard wearing and boasts an extremely effective available). Unlike serrated steel, the anti-slip surface for guarding options to allow safe handling/contact. does not impact load carrying capacity.

commonly used in industrial applications. It is very where by-products are commonly caught by serrations, and is hence very often utilised by the coefficient of friction (NATA laboratory test report food industry. This surface option can also be used

utilised for guarding and architectural features in a variety of applications. Whilst the aesthetics of the product are improved, the anti-slip properties are not as profound as the other options available.









## **Grat EX**®

## **GratEX® Square Mesh**



# **GratEX® Square Mesh**



# **GratEX® Square Mesh**

### Safe Load & Deflection Charts (mm) - Uniform and Concentrated Line Loads

Mesh Grid	F-MG30(38/38)S  F-MG30(38/38)S  400  800  F-MG30(38/38)S  400  800  F-MG38(38/38)S  400  600  38X38 38X38 38X6 800		Span (mm)				Co					eflection – Deflec		n)			
Gila	Details	(m	m)	3	5	8	10	15	20	25	30	40	50	60	80	90	100
F-MG2	25(38/38	3)S															
			ΔU	0.32	0.55	0.87	1.12	1.67	2.23	2.79	3.35	4.46	5.58	6.69	8.93	10.04	11.15
		400	ΔC	1.22	2.05	3.27	4.12	6.17	8.23	10.29	12.35	16.46					
			ΔU	1.28	2.15	3.43	4.31	6.47	8.63	10.79	12.95	17.26					
38X38	25X6	600	ΔC	3.50	5.85	9.33	11.72	17.57									
			ΔU	4.15	6.94	11.09	13.88										
		800	ΔC	8.30	13.85												
F-MG <sup>2</sup>	30(38/38	3)5															
			ΔU	0.24	0.42	0.65	0.85	1.26	1.69	2.11	2.54	3.38	4.23	5.07	6.77	7.60	8.44
		400	ΔC	0.99	1.67	2.67	3.37	5.04	6.73	8.41	10.10	13.46		3.27			
			ΔU	0.99	1.67	2.66	3.35	5.02	6.70	8.36	10.04	13.38					
38X38	30X6	600	ΔC	2.72	5.46	7.28	9.13	13.68									
			ΔU	3.15	5.28	8.43	10.56										
		800	ΔC	6.25	10.44												
F-MG	38(38/38	5)C															
T MO.	36(36/36	3)3	ΔU	0.12	0.22	0.34	0.45	0.67	0.90	1.12	1.35	1.79	2.25	2.69	3.6	4.04	4.48
		400	ΔC	0.62	1.05	1.67	2.12	3.17	4.23	5.29	6.35	8.46	10.58	12.69	16.93	19.04	4.40
			ΔU	0.55	0.94	1.49	1.88	2.82	3.77	4.70	5.65	7.52	9.42	11.29	15.07	16.94	18.81
		600	ΔC	1.54	2.59	4.13	5.18	7.77	10.37	12.95	15.55	,,,,	, , <u>-</u>	>	13117		
			ΔU	1.69	2.84	4.53	5.68	8.52	11.37	14.2	17.05						
38X38	38X6	6 800	ΔC	3.28	5.49	8.77	10.98	16.47									
			ΔU	4.16	6.95	11.11	13.92										
		1000	ΔC	6.78	11.32	18.1											
		4000	ΔU	8.76	14.62												
		1200	ΔC	11.58	19.32												
F-MG'	50(50/50	D)S															
			ΔU	0.08	0.15	0.23	0.32	0.47	0.63	0.79	0.95	1.26	1.58	1.89	2.53	2.84	3.15
		400	ΔC	0.31	0.34	0.85	1.08	1.62	2.17	2.70	3.25	4.32	5.42	6.49	8.67	9.74	11.91
			ΔU	0.09	0.17	0.25	0.34	0.51	0.69	0.85	1.03	1.36	1.72	2.05	2.75	3.08	3.41
		600	ΔC	0.88	1.49	2.37	2.98	4.47	5.97	7.45	8.95	11.92	14.92	17.89			
		000	ΔU	0.28	0.49	0.77	0.98	1.47	1.97	2.45	2.95	3.92	4.92	6.49	8.67	8.84	9.81
FOVE	5077	800	ΔC	1.82	3.05	4.87	6.12	9.17	12.23	15.29	18.35						
50X50	50X6	1000	ΔU	2.18	3.65	5.83	7.32	10.97	14.63	18.29							
		1000	ΔC	3.62	6.05	9.67	12.12	14.63									
		1200	ΔU	4.56	10.1	12.18	16.15										
		1200	ΔC	6.05	13.69	16.15											
		1400	ΔU	8.2	16.15												
		00	ΔC	9.68													



## **GratEX® Square Mesh Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- 3.1 The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- 6.1 All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

### **Product System**

#### 7.0 Manufacturing Process

- 7.1 All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- 7.2 Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- 7.7 All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- 7.8 Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- 7.9 The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- 7.11 Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

Ordering Information	Code
Nominate the type of grating required	F-MG = GratEX® Moulded Grating
	13, 15, 20, 23, 25, 30, 38, 50, 53, 55 and 63
	(38/38) = 38mm x 38mm (40/40) = 40mm x 40mm (50/50) = 50mm x 50mm (79/79) = 79mm x 79mm (83/83) = 83mm x 83mm
	S = Standard Square Mesh DS = Diagonal Square Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

5.	Specify the resin, material or type (see page 6)	0 = 0-Series® I = I-Series® V = V-Series®
6.	Specify the colour required *In which instance a code and name of the selected colour must be mentioned within the description.	G = Industrial Green Y = Safety Yellow LG = Light Grey DG = Dark Grey CH = Charcoal C = Custom*
7.	Specify the surface style required	CG = Commercial Grade (Grit) Anti-Slip G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip C = Concave P = Plain(Flat)

Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as  $GratEX^{\otimes}$  is available in a variety of size panels to suit applications.

8. Nominate the panel size required	1 = 1225 mm x 3665 mm
	2 = 920 mm x 3055 mm

Please refer to Appendix 3: GratEX® Ordering Codes - page 82

# **GratEX® Heavy Duty Square Mesh**





Mesh Load Grid Bar	Span			Co				/m²) – D C (kN/m)			n)			
Details	(mm)	5	8	10	15	20	25	30	40	50	60	80	90	100

F-MG!	F-MG50(38/38)HDS																
	3 50X10	400	ΔU	0.03	0.05	0.10	0.13	0.15	0.18	0.23	0.31	0.46	0.59	0.71	0.84	0.94	1.07
		400	ΔC	0.15	0.23	0.38	0.48	0.61	0.71	0.94	1.20	1.86	2.37	2.85	3.34	3.79	
		600	ΔU	0.15	0.25	0.41	0.51	0.66	0.76	0.99	1.25	1.96	2.52	3.00	3.51	4.02	
		600	ΔC	0.41	0.66	1.07	1.35	1.73	2.01	2.67	3.36						
38X38		800	ΔU	0.46	0.76	1.20	1.50	1.96	2.27	3.00	3.77						
30/30	30/10		ΔC	0.89	1.50	2.42	3.00	3.92									
		1000	ΔU	1.09	1.81	2.90	3.64										
		1000	ΔC	1.76	2.90												
		1200	ΔU	2.27	3.77												
			ΔC	3.00													

F-MG	50(38/38	3)HDS															
		400	ΔU	0.01	0.03	0.06	0.07	0.09	0.10	0.13	0.17	0.26	0.33	0.40	0.47	0.53	0.60
		400	ΔC	0.09	0.13	0.22	0.27	0.34	0.40	0.53	0.68	1.05	1.34	1.61	1.88	2.14	
		600	ΔU	0.09	0.14	0.23	0.29	0.37	0.43	0.56	0.70	1.11	1.42	1.70	1.98	2.27	
		600	ΔC	0.23	0.37	0.60	0.76	0.98	1.14	1.51	1.90						
38X38	60X10	800	ΔU	0.26	0.43	0.68	0.85	1.11	1.28	1.70	2.13						
30/30	60/10	800	ΔC	0.50	0.85	1.37	1.70	2.21									
		1000	ΔU	0.62	1.02	1.64	2.06										
		1000	ΔC	0.99	1.64												
		1200	ΔU	1.28	2.13												
		1200	ΔC	1.70													



## **GratEX® Heavy Duty Square Mesh Specification**

#### General

#### 1.0 Scope

The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear
- All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- 7.11 Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### Ordering Information

#### Code

- Nominate the type of grating F-MG = GratEX® Moulded Grating required
- Nominate the depth (mm) 30, 35, 50 and 60 required
- Nominate the load bar centres  $(38/38) = 38 \text{mm} \times 38 \text{mm}$ required
- Nominate the mesh type required HDS = Heavy Duty Square Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)


- Specify the resin, material or type 0 = 0-Series (see page 6)
  - I = I-Series® V = V-Series®
- Specify the colour required
  - \*In which instance a code and name of the selected colour must be mentioned LG = Light Grey within the description.
- G = Industrial Green
  - Y = Safety Yellow

  - DG = Dark Grey
  - CH = Charcoal
  - C = Custom\*
- Specify the surface style required
- CG = Commercial Grade (Grit) Anti-Slip
- G = Industrial Grade (Grit) Anti-Slip
- MG = Marine Grade (Grit) Anti-Slip
- C = Concave
- P = Plain(Flat)

Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications.

- 8. Nominate the panel size required
- 1 = 1225 mm x 3665 mm2 = 920 mm x 3055 mm

Please refer to Appendix 3: GratEX® Ordering Codes - page 82



### **Benefits of FRP**



#### No Hot Work or Welding Required

FRP is very simply modified or fabricated on site with easy to use hand tools. These can be done without the hassle of first needing to obtain hot work permits.

5.8mm 5.8mm

38.1mm




#### **Light Weight, High Strength & Easy Installation**


Treadwell 's FRP products and systems are lightweight and very manageable. FRP has specific gravity one quarter that of steel and two thirds of aluminium.




#### **Environmentally Sound**

Related to the lightweight, low need for maintenance and long design life of FRP, the reduced lifecycle cost and environmental footprint are highly sought after characteristics in the modern world. Continual resin formulation fine tuning and development can further raise this environmental profile of composites.












## **EX-Series® Integral Edge Banding**

Treadwell sets the highest standards for FRP edge banding without compromise. Treadwell offers specifiers a flexibility in design and finishes, allowing projects that consistent finish that impresses. Each project is accurately cut with computer aids before the required surface option is applied. This allows for an ultimate seamless finish that boasts quality and will endure. So much so that Treadwell guarantees this edge banding lasts up to 15 years. Rest assured of your design's longevity with Treadwell's capability in professional edge banding.







## **EnviroTREAD™ Recreational Public Infrastructure**

Treadwell has given public recreational infrastructure a new direction with EnviroTREAD™.

With the benefits of FRP in the form of grating, handrails and structural profiles, Treadwell brings life through EnviroTREAD $^{TM}$  to boardwalks, viewing platforms, public access, bridges, shelters and more.

Durable, high strength, corrosion resistant and aesthetically pleasing, EnviroTREAD™ prolongs the design life of any construction wherever it is, always reaching new heights.





### Safe Load & Deflection Charts (mm) - Uniform and Concentrated Line Loads

Mesh Grid	Load Bar	Span				Co				/m²) – D C (kN/m)						
GIId	Details	(mm)	3	5	8	10	15	20	25	30	40	50	60	80	90	100

F-MG3	30(19/19	9)M															
		400	ΔU	0.19	0.33	0.52	0.68	1.01	1.35	1.69	2.03	2.71	3.38	4.05	5.41	6.08	6.75
		400	ΔC	0.79	1.34	2.13	2.70	4.03	5.38	6.73	8.08	10.77					
30x30/	30/9	600	ΔU	0.79	1.33	2.13	2.68	4.01	5.36	6.69	8.04	10.70					
19x19	х7	600	ΔC	2.18	3.65	5.82	7.30	10.95									
		800	ΔU	2.52	4.44	6.75	8.45										
		600	ΔC	5.00	8.35												

F-MG3	38(19/19	P)M															
		400	ΔU	0.096	0.176	0.272	0.360	0.536	0.720	0.896	1.080	1.432	1.800	2.152	2.880	3.232	3.584
		400	ΔC	0.496	0.840	1.336	1.696	2.536	3.384	4.232	5.080	6.768	8.464	10.152	13.544	15.232	
		600	ΔU	0.440	0.752	1.192	1.504	2.256	3.016	3.760	4.520	6.106	7.536	9.032	12.056	13.552	15.048
		600	ΔC	1.232	2.072	3.304	4.144	6.816	8.296	10.360	12.440						
38x38/	38/9	800	ΔU	1.352	2.072	3.624	4.544	13.176	9.096	11.360	13.640						
19x19	х7	800	ΔC	2.624	4.392	7.016	8.784										
		1000	ΔU	3.328	5.560	8.888	11.136										
		1000	ΔC	5.424	9.056	14.480											
		1200	ΔU	7.008	11.696												
		1200	ΔC	9.264	15.456												

F-MG	50(25/25	5)M															
		400	ΔU	0.064	0.432	0.184	0.256	0.38	0.504	0.632	0.760	1.008	1.264	1.512	2.024	2.272	2.520
		400	ΔC	0.248	0.432	0.680	0.864	1.30	1.736	2.160	2.600	3.456	4.336	5.192	6.936	7.792	9.528
		600	ΔU	0.120	0.136	0.200	0.272	0.41	0.552	0.680	0.824	1.088	1.376	1.640	2.200	2.464	2.728
		000	ΔC	0.224	1.192	1.896	2.384	3.58	4.776	5.960	7.160	9.536	11.936	12.312			
		800	ΔU	1.456	0.392	0.616	0.784	1.18	1.576	1.960	2.360	3.136	3.936	4.712	6.296	7.072	7.848
50x50/	50x9	800	ΔC	1.744	2.440	3.896	4.896	7.34	9.784	12.232	14.680						
25x25	12x7	1000	ΔU	2.896	2.920	4.664	5.856	8.78	11.704	14.632							
		1000	ΔC	3.648	4.840	7.734	9.696	14.54									
		1200	ΔU	4.840	6.096	9.744	12.200										
		1200	ΔC	6.560	8.080	12.920											
		1400	ΔU	7.744	10.952												
		1400	ΔC		12.920												

## **GratEX® Mini Mesh Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- 3.1 The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- 6.1 All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- 7.1 All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- 7.2 Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- 7.7 All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- 7.8 Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- 7.9 The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- 7.11 Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

**Ordering Information** 

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

	_				
1.	Nominate required	the typ	oe of gr	rating	F-MG = GratEX® Moulded Grating
2.	Nominate required	the	depth	(mm)	25, 30, 38 and 50

Code

3. Nominate the load bar centres  $(14/14) = 14 \text{mm} \times 14 \text{mm}$ required  $(19/19) = 19 \text{mm} \times 19 \text{mm}$  $(20/20) = 20 \text{mm} \times 20 \text{mm}$  $(25/25) = 25 \text{mm} \times 25 \text{mm}$ 

4. Nominate the mesh type required M = Mini Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

5. Specify the resin, material or type O = O-Series® (see page 6) I = I-Series® V = V-Series®

6. Specify the colour required G = Industrial Green

\*In which instance a code and name of the selected colour must be mentioned within the description.

G = Industrial Green
Y = Safety Yellow
LG = Light Grey
DG = Dark Grey
CH = Charcoal
C = Custom\*

Specify the surface style required CG = Commercial Grade (Grit)Anti-Slip G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip C = ConcaveP = Plain(Flat)


Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as  $GratEX^{\otimes}$  is available in a variety of size panels to suit applications.


8. Nominate the panel size required 1 = 1247 mm x 3687 mm2 = 1527 mm x 3007 mm


Please refer to Appendix 3: GratEX® Ordering Codes - page 82



## **GratEX® Micro Mesh**









## **Anti-Slip Testing & Compliance**

EX-Series® grating can be designed and suplied compliant to anti-slip wet and dry resistance as outlined in AS 4586-2013.

Treadwell's anti-slip grating properties can reduce onsite slip and trip injuries. FRP grating has a higher slip resistance when compared to metal, wood or concrete tiled surfaces.

## **GratEX® Micro Mesh Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- 3.1 The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- 6.1 All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- 7.1 All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- 7.2 Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- 7.7 All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- 7.8 Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- 7.9 The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- 7.11 Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### Ordering Information Code

- 1. Nominate the type of grating requiredF-MG = GratEX® Moulded Grating
- 2. Nominate the depth (mm) required 25, 30 and 38
- 3. Nominate the load bar  $centres(13/13) = 13mm \times 13mm$  required
- 4. Nominate the mesh type required MM = Micro Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash  $(\cdot)$ 

- 5. Specify the resin, material or type  $O = O\text{-Series}^{\circ}$  (see page 6)  $I = I\text{-Series}^{\circ}$   $V = V\text{-Series}^{\circ}$
- 6. Specify the colour required G =

  \*In which instance a code and name of Y =

\*In which instance a code and name of Y = Safety Yellow the selected colour must be mentioned LG = Light Grey within the description. DG = Dark Grey

G = Industrial Green
of Y = Safety Yellow

DG = Dark Grey
CH = Charcoal
C = Custom\*

7. Specify the surface style required

CG = Commercial Grade (Grit) Anti-Slip

G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip

C = Concave P = Plain(Flat)

Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as  $GratEX^{\otimes}$  is available in a variety of size panels to suit applications.


8. Nominate the panel size required


1 = 1225 mm x 3665 mm 2 = 920 mm x 3055 mm


Please refer to Appendix 3: GratEX® Ordering Codes - page 82




## **GratEX® Rectangular Mesh**









### **Benefits of FRP**



#### **Long Term Cost Benefits**

Long service life, minimal maintenance costs and low installation costs all combine to provide a very competitive solution over time.



### **Non-Conductive & RF Transmission Transparent**

FRP is transparent to radio frequency transmission and is non-conductive in nature. This makes the material ideal for applications that need to avoid electrical currents and radio frequency.

## **GratEX® Rectangular Mesh Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- 3.1 The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- 6.1 All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- 7.1 All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- 7.2 Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- 7.7 All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- 7.8 Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- 7.9 The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- 7.11 Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### Ordering Information Code

- Nominate the type of grating F-MG = GratEX® Moulded Grating required
- Nominate the depth (mm) 25, 30 and 38 required
- 3. Nominate the load bar centres  $(25/100) = 25 \,\mathrm{mm} \,\mathrm{x} \, 100 \,\mathrm{mm}$  required  $(38/100) = 38 \,\mathrm{mm} \,\mathrm{x} \, 100 \,\mathrm{mm}$   $(25/152) = 25 \,\mathrm{mm} \,\mathrm{x} \, 152 \,\mathrm{mm}$   $(38/152) = 38 \,\mathrm{mm} \,\mathrm{x} \, 152 \,\mathrm{mm}$   $(60/220) = 60 \,\mathrm{mm} \,\mathrm{x} \, 220 \,\mathrm{mm}$
- Nominate the mesh type R = Standard Rectangular Mesh required

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

- 5. Specify the resin, material or type O = O-Series®
  (see page 6) I = I-Series®
  V = V-Series®
- 6. Specify the colour required G = Industrial Green

  \*In which instance a code and name of Y = Safety Yellow
  the selected colour must be mentioned LG = Light Grey
  within the description. DG = Dark Grey

  CH = Charcoal
- Z. Specify the surface style required CG = Commercial Grade (Grit)
  Anti-Slip
  G = Industrial Grade (Grit) Anti-Slip
  MG = Marine Grade (Grit) Anti-Slip
  C = Concave
  P = Plain(Flat)

C = Custom\*


Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications.

8. Nominate the panel size required 1 = 1225 mm x 3665 mm 2 = 920 mm x 3055 mm

Please refer to Appendix 3: GratEX® Ordering Codes - page 89



## **GratEX® Heavy Duty Rectangular Mesh**





## LadderEX® FRP Ladders

LadderEX® is the choice alternative to metallic ladders and cage systems, providing superior corrosion resistance and electrical transparency. Even in complete submersion applications, our FRP ladders have outlasted aluminium and steel and required little maintenance or care.

The product range in Treadwell's ladder and platform systems include fibreglass platforms, fibreglass ladders, fibreglass caged ladders, FRP walkways and other such customisations in FRP based configurations which are offered in the following categories:

- Complete FRP Access Fibreglass Platforms Structure
- Fibreglass Caged Ladder System

## **GratEX® Heavy Duty Rectangular Mesh Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- 3.1 The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- 6.1 All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- 7.1 All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- 7.2 Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- 7.7 All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- 7.8 Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- 7.9 The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- 7.11 Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### Ordering Information Code

- Nominate the type of grating F-MG = GratEX® Moulded Grating required
- Nominate the depth (mm) 25, 38, and 50 required
  - Nominate the load bar centres  $(25/50) = 25 \text{mm} \times 50 \text{mm}$ required  $(25/100) = 25 \text{mm} \times 100 \text{mm}$
- 4. Nominate the mesh type required HDR = Heavy Duty Rectangular

  Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

- Specify the resin, material or type 0 = 0-Series<sup>®</sup> (see page 6) I = I-Series<sup>®</sup>
- V = V-Series®
- 6. Specify the colour required G = Industrial Green

  \*In which instance a code and name of Y = Safety Yellow
  the selected colour must be mentioned LG = Light Grey
  within the description.

  DG = Dark Grey

DG = Dark Grey CH = Charcoal C = Custom\*

- 7. Specify the surface style required
- CG = Commercial Grade (Grit)Anti-Slip
- G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip C = Concave
- C = Concave P = Plain(Flat)

Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as  $GratEX^{\otimes}$  is available in a variety of size panels to suit applications.

8. Nominate the panel size required 1 = 1225 mm x 3665 mm 2 = 920 mm x 3055 mm

Please refer to Appendix 3: GratEX® Ordering Codes - page 82

## GratEX® Solid Surface Mesh

### **GratEX® Solid Surface Options**

Unlike serrated steel grating, the compared to other surface finishes. anti-slip surface does not impact on load carrying capacity.

Anti-Slip Surface (Standard). This Chequer Plate Surface. Offers a less Diamond Plate. Diamond Plate Plain Surface. This surface is a nonsurface is most commonly used in aggressive anti-slip flooring solution surface is a popular cover option industrial applications. It is very which does not trap as much dirt that offers less traction. It is ideal utilised in applications where a hard-wearing and has an extremely or grime as grit types and can be in environments where grit and robust and anti-corrosive substrate is effective coefficient of friction (NATA cleaned much easier. These options grime can be potentially trapped in required for a primary floor covering. laboratory test report available). also offer superior aesthetics conventional grating. The diamond pattern is aesthetically pleasing and industrial flooring applications, it easy to clean.


stock option and is most commonly Used commonly in commercial and successfully provides lightweight and cost-effective solutions.














### **Benefits of FRP**



#### No Protective Coating Required


Treadwell's unique surface finishing system ensures UV stability in exposed applications, directly eliminating the need for costly surface treatment.





#### **Corrosion, Rust & Rot Proof**

Treadwell's superior resin systems offer exceptional resistance to acids, salts and alkalis. At the same time, our FRP systems are rot and termite proof.


## **GratEX® Solid Surface Mesh**













# GratEX® Solid Surface Mesh

### Safe Load & Deflection Charts (mm) - Uniform and Concentrated Line Loads

Mesh Grid	Load Bar	Span				Cı		rm load - ted line l								
	Details	(mm)	3	5	8	10	15	20	25	30	40	50	60	80	90	100

F-MG2	25(38/38	3)(3)F, F-I	MG25(38	8/38)(5)I	F												
		400	ΔU	0.26	0.44	0.70	0.90	1.34	1.78	2.23	2.68	3.57	4.46	5.35	7.14	8.03	8.92
		400	ΔC	0.98	1.64	2.616	3.30	4.94	6.58	8.23	9.88	13.17					
20,20	25,46	600	ΔU	1.02	1.72	2.74	3.46	5.18	6.90	8.63	10.36	13.81					
38x38	25x6	600	ΔC	2.80	4.68	7.48	9.38	14.06									
		800	ΔU	3.32	5.55	8.87	11.10										
		800	ΔC	6.64	11.08												

F-MG	38(38/38	3)(3)F, F-I	MG38(3	8/38)(5)	F												
		400	ΔU	0.96	0.18	0.27	0.36	0.54	0.72	0.90	1.08	1.43	1.80	2.15	3.23	2.88	3.58
		400	ΔC	0.50	0.84	1.34	1.7	2.54	3.38	4.23	5.08	6.77	8.46	10.15	15.53	13.54	15.05
		600	ΔU	0.44	0.75	1.19	1.5	2.26	3.02	3.76	4.52	6.02	7.54	9.03	12.06	12.06	
		000	ΔC	1.23	2.07	3.3	4.14	6.22	8.3	10.36	12.44						
38x38	38x6	800	ΔU	1.35	2.27	3.62	4.54	6.82	9.1	11.36	13.64						
00,00	3680	800	ΔC	2.62	4.39	7.02	8.78	13.18									
		1200	ΔU	3.54	5.91	9.44	11.83										
		1200	ΔC	5.76	9.62	15.39											
		1400	ΔU	7.45	12.34												
		1400	ΔC	9.84	16.42												

F-MG5	50(50/50	O)(3)F, F-	MG50(5	0/50)(5)	F												
		400	ΔU	0.06	0.12	0.18	0.26	0.38	0.50	0.63	0.76	1.01	1.26	1.51	2.02	2.27	2.52
		400	ΔC	0.25	0.27	0.68	0.86	1.3	1.74	2.16	2.6	3.46	4.34	5.19	6.94	7.79	9.53
		600	ΔU	0.07	0.14	0.2	0.27	0.41	0.55	0.68	1.03*.8	1.38	1.38	1.64			
		000	ΔC	0.7	1.19	1.9	2.38	3.58	4.78	5.96	7.16	11.94	11.94	14.31	2.20	2.46	2.73
		800	ΔU	0.22	0.39	0.62	0.78	1.18	1.58	1.96	2.36	3.94	3.94	4.71	6.30	7.07	7.85
50X50	50x6	800	ΔC	1.46	2.44	3.9	4.9	7.34	9.78	12.23	14.68						
30/30	3000	1000	ΔU	1.74	2.92	4.66	5.86	8.78	11.70	14.63							
		1000	ΔC	2.9	4.84	7.74	9.7	14.63									
		1200	ΔU	3.88	6.48	10.35	12.96										
		1200	ΔC	5.14	8.59	13.73											
		1400	ΔU	6.97	11.64												
		1400	ΔC	8.23	13.73												

## **GratEX® Solid Surface Mesh Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### **Ordering Information**

#### Code

- Nominate the type of grating F-MG = GratEX® Moulded Grating required
- Nominate the depth (mm) 20, 25, 35, 38, 50, and 60 required
- Nominate the load bar centres  $(38/38) = 38 \text{mm} \times 38 \text{mm}$ required (50/50) = 50mm x 50mm (79/79) = 79mm x 79mm

(3) = 3 mm(5) = 5 mm

Nominate the mesh type required F = Solid Surface (Flat) Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

- Specify the resin, material or type 0 = 0-Series® (see page 6)
  - I = I-Series® V = V-Series®
- Specify the colour required
  - G = Industrial Green \*In which instance a code and name of Y = Safety Yellow

the selected colour must be mentioned LG = Light Grey within the description.

DG = Dark Grey CH = CharcoalC = Custom\*

- Specify the surface style required
- CG = Commercial Grade (Grit) Anti-Slip
- G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip

C = ConcaveP = Plain(Flat)

Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications.


Nominate the panel size required


1 = 1225 mm x 3665 mm 2 = 920 mm x 3055 mm

Please refer to Appendix 3: GratEX® Ordering Codes - page 82



## **GratEX® Heavy Duty Solid Surface Mesh**







# **EX-Series® Integral Kickplates**

Treadwell sets the highest standards for grating kickplates without compromise. With the provision of high quality grating kickplates, Treadwell offers specifiers a flexibility in design and finishes, allowing projects that consistent finish that impresses. Each project is accurately cut before the required surface option is applied. This allows for an ultimate seamless finish that boasts quality and will endure. Rest assured of your design's longevity with Treadwell's high quality grating kickplates.

## **GratEX® Heavy Duty Solid Surface Mesh Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### **Ordering Information** Code

- Nominate the type of grating F-MG = GratEX® Moulded Grating required
- Nominate depth the (mm) 30, 35, 50 and 60 required
- Nominate the load bar centres  $(38/38) = 38 \text{mm} \times 38 \text{mm}$ required

(3) = 3 mm(5) = 5 mm

Nominate the mesh type required HDF = Heavy Duty Solid Surface (Flat) Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

Specify the resin, material or type 0 = 0-Series (see page 6)

I = I-Series® V = V-Series®

Specify the colour required

\*In which instance a code and name of the selected colour must be mentioned LG = Light Grey within the description.

G = Industrial Green Y = Safety Yellow

DG = Dark Grey CH = Charcoal C = Custom\*

Specify the surface style required

CG = Commercial Grade (Grit) Anti-Slip

G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip

CH = Chequer Plate P = Plain(Flat)

Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications.


Nominate the panel size required 1 = 1225 mm x 3665 mm

2 = 920 mm x 3055 mm

Please refer to Appendix 3: GratEX® Ordering Codes - page 82

## **GratEX® Stair Treads**





### Can I Use FRP for Stair Treads?

Treadwell's range of GratEX® Stair Treads includes both open surface and closed surface options, and a range of surface patterns, colour and leading edge nosing options.


All GratEX® Premium and Standard Stair Tread options are moulded with the Solid Leading Edge Nosing as an integrated single stage operation. This increases the rigidity and durability of the entire leading edge, ensuring reliable performance in high traffic scenarios. All the treads with abrasive leading edge nosings are manufactured to conform to AS 1657 – 2018.

The GratEX® Stair Tread nosings are typically stocked in colours that contrast by 30% with the primary tread colour as per AS 1657 – 2018. This ensures maximum visual awareness of the stair treads forward edge for personnel utilising the stairways and consequently enhancing the OHS safety ratings.


Treadwell recommends that leading edge nosings are specified when ordering  $GratEX^{\otimes}$  Stair Treads as the safety risks associated with elevated work areas or walkways are significantly increased without them.

**NOTE:** A bearing surface of at least 40mm is recommended at either side of GratEX® Stair Treads. Compliance with AS 1657 – 2018 requires a Tread depth of > 225mm.

Selecting a tread with lasting non-slip properties, resilience to corrosion and proven long term cost advantages can help you enhance safety in the workplace by reducing the chance of slips, trips and falls.



## **GratEX® Stair Treads**



### **Ordering Information**

- 1. Nominate the type of grating required
- 2. Choose the depth (mm) required
- 3. Select the load bar centres required
- 4. Select the mesh type required

#### Code

F-MG = GratEX® Moulded Grating

25, 30, 38, 50

 $(13/13) = 13 \text{mm} \times 13 \text{mm}$   $(25/25) = 25 \text{mm} \times 25 \text{mm}$   $(19/19) = 19 \text{mm} \times 19 \text{mm}$   $(38/38) = 38 \text{mm} \times 38 \text{mm}$   $(20/20) = 20 \text{mm} \times 20 \text{mm}$   $(50/50) = 50 \text{mm} \times 50 \text{mm}$ 

S = Square mesh R = Rectangular M = Mini Mesh F = Solid Surface MM = Micro Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

- 5. Select the resin, material or type (see page 6)
- 6. Choose the tread colour required (\*In which instance a code and name of the selected colour must be mentioned within the description)
- 7. Select the surface style required

0 = 0-Series<sup>®</sup>

I = I-Series®

V = V-Series®

 $\begin{array}{ll} G = Industrial \ Green \\ Y = Safety \ Yellow \\ LG = Light \ Grey \end{array} \qquad \begin{array}{ll} DG = Dark \ Grey \\ CH = Charcoal \\ C = Custom^* \end{array}$ 

CG = Commercial Grade (Grit) Anti-Slip

G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip

C = Concave P = Plain (Flat) CH = Checker Plate

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

8. Nominate the stair tread type

STE = Economy STP = Premium STC = Custom STK = Kit

 Select the nosing colour required (\*In which instance a code and name of the selected colour must be mentioned within the description) (B) = Black

(H) = Chevron (two tone)

(Y) = Safety Yellow (C) = Custom\*

Note: Please specify the tread size required and the side that you require the nosing on in the description.

Minimum width: 582mm


Maximum width: 3665mm

Minimum depth: 235mm Maximum depth: 387mm

Minimum depth: 235mm Example: F-MG38(38/38)S-IGG-STP(Y)

## **GratEX® Stair Tread Kits**





### Is there a GratEX® Stair Tread Retro-fit Option?

GratEX® Stair Tread Kits offer a complete 'change out' package to replace existing stair treads and stringer bracket assemblies that have suffered premature corrosion.

Traditionally, stringer bracket assemblies are made from metallic materials which require corrosion inhibiting coatings to ensure satisfactory life span. It is typical for stair tread mounting brackets to be drilled in situ after this coating has been applied, thus compromising the integrity of this first line of defence against corrosion. It is also common for stringer brackets to be constructed of lighter walled material than other adjacent componentry such as stringers.

These kits have been adopted as a superior replacement for the originally specified equipment in many instances as well as being chosen as a long life and cost saving alternative to metallic systems in numerous new plants.

Tread kits are available in all resin systems and are supplied with M-Clips as standard. Treads can be supplied assembled ready for installation or ready for assembly onsite. Likewise, stringer support brackets can be supplied with pre-drilled mounting holes if specified. Treadwell does not recommend the use of stair treads with a thickness of less than 25mm.

## **GratEX® Landings**



# GratEX® landings are also available as a part of Treadwell's extensive range.

GratEX® landings combine the lasting non-slip properties, the resilience to corrosion and the proven long term cost advantages of GratEX® stair treads with the durable nature of GratEX® grating.

These landings are custom made for each and every application, greatly enhance visibility and reduce the wear commonly seen on landings immensely.

Contact Treadwell's technical assistance team for further details.



## **Fastening Clips & Installation Methods**



#### **Installation Accessories**

The GratEX® moulded FRP grating products are complimented by an extensive range of fixing types and installation systems. All GratEX® installation clip sets are tested and proven to function in the harshest of applications, offering you total peace of mind.

All of the GratEX $^{\odot}$  installation systems are supplied and stocked as 316 grade stainless steel with super duplex, 304 grade stainless and galvanised steel options available upon request. This flexibility means that we can provide a suitable solution for whatever chemicals or application you have.

The GratEX® clip range also includes a large range of underside clips which provides additional options when when designing substructures with the consideration of fixing methods. Refer to the StormChief® page for information on our unique range of extreme strength clip options for high wave action zones.

### **GratEX® Clip - Tops**

GratEX® Clip - Tops				
STANDARD M	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 8mm Material type: 316 st/st Threaded hole: N/A	1			1, 3, 4, 6
MINI MESH M	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 6mm Material type: 316 st/st Threaded hole: N/A	T			5,7
С	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 6mm Material type: 316 st/st Threaded hole: Yes		•		2
L	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 6.5mm Material type: 316 st/st Threaded hole: N/A				2
D	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 8.5mm Material type: 316 st/st Threaded hole: N/A	Del			1, 3, 4, 6
Е	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 8mm Material type: 316 st/st Threaded hole: N/A		•		1, 3, 4, 6
W	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 8mm Material type: 316 st/st Threaded hole: N/A		0		1, 3, 4, 6
S	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 6mm Material type: 316 st/st Threaded hole: N/A	(3)	0		5, 7
0	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 8mm Material type: 316 st/st Threaded hole: N/A	6	0		10

# **Fastening Clips & Installation Methods**

### **Clamp Underside**

J - UNIVERSAL	3D	PLAN	ELEVATION	SIDE ELEVATIO	N FASTENING OPTIONS
Hole Diameter: N/A Material type: 316 st/st Threaded hole: N/A	4		-		1, 3, 4
J - MINI-MESH	3D	PLAN	ELEVATION	SIDE ELEVATIO	N FASTENING OPTIONS
Hole Diameter: N/A Material type: 316 st/st Threaded hole: N/A	4				5
Н	3D	PLAN		ELEVATION	FASTENING OPTIONS
Hole Diameter: 8mm Material type: st/st Threaded hole: Yes	4				1, 3, 4
G	3D	PLAN		ELEVATION	FASTENING OPTIONS
Hole Diameter: 6mm Material type: st/st Threaded hole: Yes	E	1	ı		2
U	3D	PLAN		ELEVATION	FASTENING OPTIONS
Hole Diameter: 8mm Material type: 316 st/st Threaded hole: Yes	2	_	-	7	1, 3, 4
V	3D	PLAN		ELEVATION	FASTENING OPTIONS
Hole Diameter: 8mm Material type: 316 st/st Threaded hole: N/A			<b>=</b>		1, 3, 4
T	3D	PLAN		ELEVATION	FASTENING OPTIONS
Hole Diameter: Material type: Threaded hole:					1, 3, 4, 9

### **Fastening Options**

1	2	3	4	5
I	I	I	Î	Î
F-FA(SC)-M8*40-HX-SS316 Metric 8mm x 40mm, 316 Grade Stainless Steel Set Screw with Hex Head c/w nylon nut and washer.	F-FA(SC)-M6*40-HX-SS316 Metric 6mm x 40mm, 316 Grade Stainless Steel Set Screw with Hex Head c/w nylon nut and washer.	F-FA(SC)-M8*40-SH-S5316 Metric 8mm x 40mm, 316 Grade Stain- less Steel Set Screw with Socket Head c/w nylon nut and washer.	F-FA(SC)-M8*60-BH-S5316 Metric 8mm x 60mm, 316 Grade Stain- less Steel Set Screw with Button Head c/w nylon nut and washer.	F-FA(B)-M5*50-SH-S5316 Metric 5mm x 50mm, 316 Grade Stainless Steel Set Screw Socket Head c/w nylon nut.
6				10
•	î	•		T
	44444444444444444444444444444444444444		Ī	


### **Fastening Profiles Ordering Information:**

Please refer to Appendix 6a: GratEX® Fasteners Ordering Information.


#### **Fastening Clip Frequency Recommendation:**

Treadwell recommends that at least 4 GratEX® clip sets be installed per panel, regardless of size, or approximately 4 per m² for areas exceeding 1 m². If you have a unique requirement, chances are we have encountered something similar before – contact Treadwell on 1800 246 800.

# **Fixing Assembly Combinations**




## **Fixing Assembly Combinations**




### **Grat EX**®

# **Fixing Assembly Combinations**



## **Fixing Assembly Combinations**



To find the closed load bar dimension that is closest to your required dimensions, simply find the table that relates to your preferred grating type and aperture, and then locate the dimension listed which varies the least from the required dimensions. These dimensions are indicative and can be varied slightly in manufacture. The Treadwell team can provide advice on designing around grating closed load bar dimensions – please call 1800 246 800.

#### **GratEX® Square Mesh**

#### 38 x 38 Mesh Grid Load Bar Chart

#### 1568.5 3092.5 2 44.5 22 806.5 42 62 2330.5 3 82.6 23 844.6 43 1606.6 63 2368.6 83 3130.6 4 120.7 24 882.7 44 1644.7 64 2406.7 84 3168.7 5 158.8 25 920.8 45 1682.8 65 2444.8 85 3206.8 6 196.9 26 958.9 46 1720.9 66 2482.9 86 3244.9 7 235 27 997.0 47 1759.0 67 2521.0 87 3283.0 8 273.1 28 1035.1 48 1797.1 68 2559.1 88 3321.1 9 311.2 29 1073.2 49 1835.2 69 2597.2 89 3359.2 10 349.3 30 1111.3 50 1873.3 70 2635.3 90 3397.3 11 31 1149.4 1911.4 91 3435.4 387.4 51 71 2673.4 12 425.5 32 1187.5 52 1949.5 72 2711.5 92 3473.5 13 463.6 33 1225.6 53 1987.6 73 2749.6 93 3511.6 14 501.7 34 1263.7 54 2025.7 74 2787.7 94 3549.7 15 539.8 35 1301.8 55 2063.8 75 2825.8 95 3587.8 577.9 1339.9 2101.9 2863.9 96 3625.9 16 36 56 76 17 1378.0 616 37 57 2140.0 77 2902.0 3664.0 18 654.1 38 1416.1 58 2178.1 78 2940.1 98 3702.1 3740.2 19 692.2 39 1454.2 59 2216.2 79 2978.2 99 20 730.3 40 1492.3 60 2254.3 80 3016.3 100 3740.2 21 768.4 41 1530.4 61 2292.4 81 3054.4 101 3816.4

#### 40 x 40 Mesh Grid Load Bar Chart

40 Mesh	Grid	Load Ba	r Cha	rt				
mm								
46.4	22	846.4	42	1646.4	62	2446.4	82	3246.4
86.4	23	886.4	43	1686.4	63	2486.4	83	3286.4
126.4	24	926.4	44	1726.4	64	2526.4	84	3326.4
166.4	25	966.4	45	1766.4	65	2566.4	85	3366.4
206.4	26	1006.4	46	1806.4	66	2606.4	86	3406.4
246.4	27	1046.4	47	1846.4	67	2646.4	87	3446.4
286.4	28	1086.4	48	1886.4	68	2686.4	88	3486.4
326.4	29	1126.4	49	1926.4	69	2726.4	89	3526.4
366.4	30	1166.4	50	1966.4	70	2766.4	90	3566.4
406.4	31	1206.4	51	2006.4	71	2806.4	91	3606.4
446.4	32	1246.4	52	2046.4	72	2846.4	92	3646.4
486.4	33	1286.4	53	2086.4	73	2886.4	93	3686.4
526.4	34	1326.4	54	2126.4	74	2926.4	94	3726.4
566.4	35	1366.4	55	2166.4	75	2966.4	95	3766.4
606.4	36	1406.4	56	2206.4	76	3006.4	96	3806.4
646.4	37	1446.4	57	2246.4	77	3046.4	97	3846.4
686.4	38	1486.4	58	2286.4	78	3086.4	98	3886.4
726.4	39	1526.4	59	2326.4	79	3126.4	99	3926.4
766.4	40	1566.4	60	2366.4	80	3166.4	100	3966.4
806.4	41	1606.4	61	2406.4	81	3206.4	101	4006.4
	mm  46.4  86.4  126.4  166.4  206.4  246.4  326.4  366.4  446.4  526.4  566.4  646.4  726.4  766.4	mm  46.4 22 86.4 23 126.4 24 166.4 25 206.4 26 246.4 27 286.4 28 326.4 29 366.4 30 406.4 31 446.4 32 486.4 33 526.4 34 566.4 35 606.4 36 646.4 37 686.4 38 726.4 39	mm  46.4 22 846.4 86.4 23 886.4 126.4 24 926.4 166.4 25 966.4 206.4 26 1006.4 246.4 27 1046.4 286.4 28 1086.4 326.4 29 1126.4 366.4 30 1166.4 406.4 31 1206.4 446.4 32 1246.4 486.4 33 1286.4 526.4 34 1326.4 566.4 35 1366.4 606.4 36 1406.4 646.4 37 1446.4 686.4 38 1486.4 726.4 39 1526.4	mm         46.4         22         846.4         42           86.4         23         886.4         43           126.4         24         926.4         44           166.4         25         966.4         45           206.4         26         1006.4         46           246.4         27         1046.4         47           286.4         28         1086.4         48           326.4         29         1126.4         49           366.4         30         1166.4         50           406.4         31         1206.4         51           446.4         32         1246.4         52           486.4         33         1286.4         53           526.4         34         1326.4         54           566.4         35         1366.4         55           606.4         36         1406.4         56           646.4         37         1446.4         57           686.4         38         1486.4         58           726.4         39         1526.4         59           766.4         40         1566.4         60	46.4         22         846.4         42         1646.4           86.4         23         886.4         43         1686.4           126.4         24         926.4         44         1726.4           166.4         25         966.4         45         1766.4           206.4         26         1006.4         46         1806.4           246.4         27         1046.4         47         1846.4           286.4         28         1086.4         48         1886.4           326.4         29         1126.4         49         1926.4           406.4         30         1166.4         50         1966.4           406.4         31         1206.4         51         2006.4           446.4         32         1246.4         52         2046.4           486.4         33         1286.4         53         2086.4           526.4         34         1326.4         54         2126.4           566.4         35         1366.4         55         2166.4           606.4         36         1406.4         56         2206.4           646.4         37         1446.4         57	mm         46.4         22         846.4         42         1646.4         62           86.4         23         886.4         43         1686.4         63           126.4         24         926.4         44         1726.4         64           166.4         25         966.4         45         1766.4         65           206.4         26         1006.4         46         1806.4         66           246.4         27         1046.4         47         1846.4         67           286.4         28         1086.4         48         1886.4         68           326.4         29         1126.4         49         1926.4         69           366.4         30         1166.4         50         1966.4         70           406.4         31         1206.4         51         2006.4         71           446.4         32         1246.4         52         2046.4         72           486.4         33         1286.4         53         2086.4         73           526.4         34         1326.4         54         2126.4         74           566.4         35         1366.4	mm         46.4         22         846.4         42         1646.4         62         2446.4           86.4         23         886.4         43         1686.4         63         2486.4           126.4         24         926.4         44         1726.4         64         2526.4           166.4         25         966.4         45         1766.4         65         2566.4           206.4         26         1006.4         46         1806.4         66         2606.4           246.4         27         1046.4         47         1846.4         67         2646.4           286.4         28         1086.4         48         1886.4         68         2686.4           326.4         29         1126.4         49         1926.4         69         2726.4           406.4         31         1206.4         51         2006.4         70         2766.4           406.4         32         1246.4         52         2046.4         72         2846.4           486.4         33         1286.4         53         2086.4         73         2886.4           526.4         34         1326.4         54         2126.4 </th <th>mm         46.4         22         846.4         42         1646.4         62         2446.4         82           86.4         23         886.4         43         1686.4         63         2486.4         83           126.4         24         926.4         44         1726.4         64         2526.4         84           166.4         25         966.4         45         1766.4         65         2566.4         85           206.4         26         1006.4         46         1806.4         66         2606.4         86           246.4         27         1046.4         47         1846.4         67         2646.4         87           286.4         28         1086.4         48         1886.4         68         2686.4         88           326.4         29         1126.4         49         1926.4         69         2726.4         89           366.4         30         1166.4         50         1966.4         70         2766.4         90           406.4         31         1206.4         51         2006.4         71         2806.4         91           446.4         32         1246.4         52</th>	mm         46.4         22         846.4         42         1646.4         62         2446.4         82           86.4         23         886.4         43         1686.4         63         2486.4         83           126.4         24         926.4         44         1726.4         64         2526.4         84           166.4         25         966.4         45         1766.4         65         2566.4         85           206.4         26         1006.4         46         1806.4         66         2606.4         86           246.4         27         1046.4         47         1846.4         67         2646.4         87           286.4         28         1086.4         48         1886.4         68         2686.4         88           326.4         29         1126.4         49         1926.4         69         2726.4         89           366.4         30         1166.4         50         1966.4         70         2766.4         90           406.4         31         1206.4         51         2006.4         71         2806.4         91           446.4         32         1246.4         52

Note: The figures are indicative or an estimate only. This is a guide and an allowance for manufacturing tolerances (page 70) should be made.

#### 50.8 x 50.8 Mesh Grid Load Bar Chart

No. of Bars	mm								
2	57.2	22	1073.2	42	2089.2	62	3105.2	82	4121.2
3	108.0	23	1124.0	43	2140.0	63	3156.0	83	4172.0
4	158.8	24	1174.8	44	2190.8	64	3206.8	84	4222.8
5	209.6	25	1225.6 1225.6t	45	2241.6	65	3257.6	85	4273.6
6	260.4	26	1276.4	46	2292.4	66	3308.4	86	4324.4
7	311.2	27	1327.2	47	2343.2	67	3359.2	87	4375.2
8	362.0	28	1378.0	48	2394.0	68	3410.0	88	4426.0
9	412.8	29	1428.8	49	2444.8	69	3460.8	89	4476.8
10	463.6	30	1479.6	50	2495.6	70	3511.6	90	4527.6
11	514.4	31	1530.4	51	2546.4	71	3562.4	91	4578.4
12	565.2	32	1581.2	52	2597.2	72	3613.2	92	4629.2
13	616.0	33	1632.0	53	2648.0	73	3664.0	93	4680.0
14	666.8	34	1682.8	54	2698.8	74	3714.8	94	4730.8
15	717.6	35	1733.6	55	2749.6	75	3765.6	95	4781.6
16	768.4	36	1784.4	56	2800.4	76	3816.4	96	4832.4
17	819.2	37	1835.2	57	2851.2	77	3867.2	97	4883.2
18	870.0	38	1886.0	58	2902.0	78	3918.0	98	4934.0
19	920.8	39	1936.8	59	2952.8	79	3968.8	99	4984.8
20	971.6	40	1987.6	60	3003.6	80	4019.6	100	5035.6
21	1022.4	41	2038.4	61	3054.4	81	4070.4	101	5086.4

#### 79 x 79 Mesh Grid Load Bar Chart

No. of Bars	mm								
2	85.4	22	1665.4	42	3245.4	62	4825.4	82	6405.4
3	164.4	23	1744.4	43	3324.4	63	4904.4	83	6484.4
4	243.4	24	1823.4	44	3403.4	64	4983.4	84	6563.4
5	322.4	25	1902.4	45	3482.4	65	5062.4	85	6642.4
6	401.4	26	1981.4	46	3561.4	66	5141.4	86	6721.4
7	480.4	27	2060.4	47	3640.4	67	5220.4	87	6800.4
8	559.4	28	2139.4	48	3719.4	68	5299.4	88	6879.4
9	638.4	29	2218.4	49	3798.4	69	5378.4	89	6958.4
10	717.4	30	2297.4	50	3877.4	70	5457.4	90	7037.4
11	796.4	31	2376.4	51	3956.4	71	5536.4	91	7116.4
12	875.4	32	2455.4	52	4035.4	72	5615.4	92	7195.4
13	954.4	33	2534.4	53	4114.4	73	5694.4	93	7274.4
14	1033.4	34	2613.4	54	4193.4	74	5773.4	94	7353.4
15	1112.4	35	2692.4	55	4272.4	75	5852.4	95	7432.4
16	1191.4	36	2771.4	56	4351.4	76	5931.4	96	7511.4
17	1270.4	37	2850.4	57	4430.4	77	6010.4	97	7590.4
18	1349.4	38	2929.4	58	4509.4	78	6089.4	98	7669.4
19	1428.4	39	3008.4	59	4588.4	79	6168.4	99	7748.4
20	1507.4	40	3087.4	60	4667.4	80	6247.4	100	7827.4
21	1586.4	41	3166.4	61	4746.4	81	6326.4	101	7906.4
	formon								



### **GratEX® Heavy Duty Mesh**

#### 38.1 x 38.1 Heavy Duty Mesh Grid Load Bar Chart

#### 80 x 80 Mesh Grid Load Bar Chart

No.of Bars	mm								
2	86.4	12	886.4	22	1686.4	32	2486.4	42	3286.4
3	166.4	13	966.4	23	1766.4	33	2566.4	43	3366.4
4	246.4	14	1046.4	24	1846.4	34	2646.4	44	3446.4
5	326.4	15	1126.4	25	1926.4	35	2726.4	45	3526.4
6	406.4	16	1206.4	26	2006.4	36	2806.4	46	3606.4
7	486.4	17	1286.4	27	2086.4	37	2886.4	47	3686.4
8	566.4	18	1366.4	28	2166.4	38	2966.4	48	3766.4
9	646.4	19	1446.4	29	2246.4	39	3046.4	49	3846.4
10	726.4	20	1526.4	30	2326.4	40	3126.4	50	3926.4
11	806.4	21	1606.4	31	2406.4	41	3206.4	51	4006.4

No.of Bars	mm								
2	48.6	22	810.6	42	1572.6	62	2334.6	82	3096.6
3	86.7	23	848.7	43	1610.7	63	2372.7	83	3134.7
4	124.8	24	886.8	44	1648.8	64	2410.8	84	3172.8
5	162.9	25	924.9	45	1686.9	65	2448.9	85	3210.9
6	201.0	26	963.0	46	1725.0	66	2487.0	86	3249.0
7	239.1	27	1001.1	47	1763.1	67	2525.1	87	3287.1
8	277.2	28	1039.2	48	1801.2	68	2563.2	88	3325.2
9	315.3	29	1077.3	49	1839.3	69	2601.3	89	3363.3
10	353.4	30	1115.4	50	1877.4	70	2639.4	90	3401.4
11	391.5	31	1153.5	51	1915.5	71	2677.5	91	3439.5
12	429.6	32	1191.6	52	1953.6	72	2715.6	92	3477.6
13	467.7	33	1229.7	53	1991.7	73	2753.7	93	3515.7
14	505.8	34	1267.8	54	2029.8	74	2791.8	94	3553.8
15	543.9	35	1305.9	55	2067.9	75	2829.9	95	3591.9
16	582.0	36	1344.0	56	2106.0	76	2868.0	96	3630.0
17	620.1	37	1382.1	57	2144.1	77	2906.1	97	3668.1
18	658.2	38	1420.2	58	2182.2	78	2944.2	98	3706.2
19	696.3	39	1458.3	59	2220.3	79	2982.3	99	3744.3
20	734.4	40	1496.4	60	2258.4	80	3020.4	100	3782.4
21	772.5	41	1534.5	61	2296.5	81	3058.5	101	3820.5

Note: The figures are indicative or an estimate only. This is a guide and an allowance for manufacturing tolerances (page 70) should be made.

#### **GratEX® Mini-Mesh**

#### 19.05 x 19.05 Mini Mesh Grid Load Bar Chart

No.of Bars	mm																		
2	26.1	12	216.6	22	407.1	32	597.6	42	788.0	52	978.5	62	1169.1	72	1359.6	82	1550.1	92	1740.6
3	45.1	13	235.6	23	426.1	33	616.6	43	807.1	53	997.6	63	1188.1	73	1378.6	83	1569.1	93	1759.6
4	64.2	14	254.7	24	445.2	34	635.7	44	826.1	54	1016.7	64	1207.2	74	1397.7	84	1588.2	94	1778.7
5	83.2	15	273.7	25	464.2	35	654.7	45	845.2	55	1035.7	65	1226.2	75	1416.7	85	1607.2	95	1797.7
6	102.3	16	292.8	26	483.3	36	673.8	46	864.2	56	1054.8	66	1245.3	76	1435.8	86	1626.3	96	1816.8
7	121.3	17	311.8	27	502.3	37	692.8	47	883.3	57	1073.8	67	1264.3	77	1454.8	87	1645.3	97	1835.8
8	140.4	18	330.9	28	521.4	38	711.9	48	902.3	58	1092.9	68	1283.4	78	1473.9	88	1664.4	98	1854.9
9	159.4	19	349.9	29	540.4	39	730.9	49	921.4	59	1111.9	69	1302.4	79	1492.9	89	1683.4	99	1873.9
10	178.5	20	369.0	30	559.5	40	750.0	50	940.4	60	1131.0	70	1321.5	80	1512.0	90	1702.5	100	1893.0
11	197.5	21	388.0	31	578.5	41	769.0	51	959.5	61	1150.0	71	1340.5	81	1531.0	91	1721.5	101	1912.0

**GratEX® Mini-Mesh** 

#### 20 x 20 Mini Mesh Grid Load Bar Chart

No. of Bars	mm																				
2	27.0	20	387.0	38	747.0	56	1107.0	74	1467.0	92	1827.0	110	2187.0	128	2547.0	146	2907.0	164	3267.0	182	3627.0
3	47.0	21	407.0	39	767.0	57	1127.0	75	1487.0	93	1847.0	111	2207.0	129	2567.0	147	2927.0	165	3287.0	183	3647.0
4	67.0	22	427.0	40	787.0	58	1147.0	76	1507.0	94	1867.0	112	2227.0	130	2587.0	148	2947.0	166	3307.0	184	3667.0
5	87.0	23	447.0	41	807.0	59	1167.0	77	1527.0	95	1887.0	113	2247.0	131	2607.0	149	2967.0	167	3327.0	185	3687.0
6	107.0	24	467.0	42	827.0	60	1187.0	78	1547.0	96	1907.0	114	2267.0	132	2627.0	150	2987.0	168	3347.0	186	3707.0
7	127.0	25	487.0	43	847.0	61	1207.0	79	1567.0	97	1927.0	115	2287.0	133	2647.0	151	3007.0	169	3367.0	187	3727.0
8	147.0	26	507.0	44	867.0	62	1227.0	80	1587.0	98	1947.0	116	2307.0	134	2667.0	152	3027.0	170	3387.0	188	3747.0
9	167.0	27	527.0	45	887.0	63	1247.0	81	1607.0	99	1967.0	117	2327.0	135	2687.0	153	3047.0	171	3407.0	189	3767.0
10	187.0	28	547.0	46	907.0	64	1267.0	82	1627.0	100	1987.0	118	2347.0	136	2707.0	154	3067.0	172	3427.0	190	3787.0
11	207.0	29	567.0	47	927.0	65	1287.0	83	1647.0	101	2007.0	119	2367.0	137	2727.0	155	3087.0	173	3447.0	191	3807.0
12	227.0	30	587.0	48	947.0	66	1307.0	84	1667.0	102	2027.0	120	2387.0	138	2747.0	156	3107.0	174	3467.0	192	3827.0
13	247.0	31	607.0	49	967.0	67	1327.0	85	1687.0	103	2047.0	121	2407.0	139	2767.0	157	3127.0	175	3487.0	193	3847.0
14	267.0	32	627.0	50	987.0	68	1347.0	86	1707.0	104	2067.0	122	2427.0	140	2787.0	158	3147.0	176	3507.0	194	3867.0
15	287.0	33	647.0	51	1007.0	69	1367.0	87	1727.0	105	2087.0	123	2447.0	141	2807.0	159	3167.0	177	3527.0	195	3887.0
16	307.0	34	667.0	52	1027.0	70	1387.0	88	1747.0	106	2107.0	124	2467.0	142	2827.0	160	3187.0	178	3547.0	196	3907.0
17	327.0	35	687.0	53	1047.0	71	1407.0	89	1767.0	107	2127.0	125	2487.0	143	2847.0	161	3207.0	179	3567.0	197	3927.0
18	347.0	36	707.0	54	1067.0	72	1427.0	90	1787.0	108	2147.0	126	2507.0	144	2867.0	162	3227.0	180	3587.0	198	3947.0
19	367.0	37	727.0	55	1087.0	73	1447.0	91	1807.0	109	2167.0	127	2527.0	145	2887.0	163	3247.0	181	3607.0	199	3967.0

Note: The figures are indicative or an estimate only. This is a guide and an allowance for manufacturing tolerances (page 70) should be made.

#### 25.4 x 25.4 Mini Mesh Grid Load Bar Chart

No. of Bars	mm																				
2	33.4	16	389.0	30	744.6	44	1100.2	58	1455.8	72	1811.4	86	2167.0	100	2522.6	114	2878.2	128	3233.8	142	3589.4
3	58.8	17	414.4	31	770.0	45	1125.6	59	1481.2	73	1836.8	87	2192.4	101	2548.0	115	2903.6	129	3259.2	143	3614.8
4	84.2	18	439.8	32	795.4	46	1151.0	60	1506.6	74	1862.2	88	2217.8	102	2573.4	116	2929.0	130	3284.6	144	3640.2
5	109.6	19	465.2	33	820.8	47	1176.4	61	1532.0	75	1887.6	89	2243.2	103	2598.8	117	2954.4	131	3310.0	145	3665.6
6	135.0	20	490.6	34	846.2	48	1201.8	62	1557.4	76	1913.0	90	2268.6	104	2624.2	118	2979.8	132	3335.4	146	3691.0
7	160.4	21	516.0	35	871.6	49	1227.2	63	1582.8	77	1938.4	91	2294.0	105	2649.6	119	3005.2	133	3360.8	147	3716.4
8	185.8	22	541.4	36	897.0	50	1252.6	64	1608.2	78	1963.8	92	2319.4	106	2675.0	120	3030.6	134	3386.2	148	3741.8
9	211.2	23	566.8	37	922.4	51	1278.0	65	1633.6	79	1989.2	93	2344.8	107	2700.4	121	3056.0	135	3411.6	149	3767.2
10	236.6	24	592.2	38	947.8	52	1303.4	66	1659.0	80	2014.6	94	2370.2	108	2725.8	122	3081.4	136	3437.0	150	3792.6
11	262.0	25	617.6	39	973.2	53	1328.8	67	1684.4	81	2040.0	95	2395.6	109	2751.2	123	3106.8	137	3462.4	151	3818.0
12	287.4	26	643.0	40	998.6	54	1354.2	68	1709.8	82	2065.4	96	2421.0	110	2776.6	124	3132.2	138	3487.8	152	3843.4
13	312.8	27	668.4	41	1024.0	55	1379.6	69	1735.2	83	2090.8	97	2446.4	111	2802.0	125	3157.6	139	3513.2	153	3868.8
14	338.2	28	693.8	42	1049.4	56	1405.0	70	1760.6	84	2116.2	98	2471.8	112	2827.4	126	3183.0	140	3538.6	154	3894.2
15	363.6	29	719.2	43	1074.8	57	1430.4	71	1786.0	85	2141.6	99	2497.2	113	2852.8	127	3208.4	141	3564.0	155	3919.6



### GratEX® Micro Mesh Micro Mesh Grid Load Bar Chart

No. of Bars	mm				(Len	gth)									(Widt	h)			
2	18.8	34	425.0	66	828.8	98	1234.8	130	1641.0	162	2044.8	194	2450.8	226	2857.0	258	3260.8	290	3666.8
3	30.8	35	436.8	67	843.0	99	1246.8	131	1652.8	163	2059.0	195	2462.8	227	2868.8	259	3275.0	291	3678.8
4	45.0	36	448.8	68	854.8	100	1261.0	132	1664.8	164	2070.8	196	2477.0	228	2880.8	260	3286.8	292	3693.0
5	56.8	37	463.0	69	866.8	101	1272.8	133	1679.0	165	2082.8	197	2488.8	229	2895.0	261	3298.8	293	3704.8
6	68.8	38	474.8	70	881.0	102	1284.8	134	1690.8	166	2097.0	198	2500.8	230	2906.8	262	3313.0	294	3716.8
7	83.0	39	486.8	71	892.8	103	1299.0	135	1702.8	167	2108.8	199	2515.0	231	2918.8	263	3324.8	295	3731.0
8	94.8	40	501.0	72	904.8	104	1310.8	136	1717.0	168	2120.8	200	2526.8	232	2933.0	264	3336.8	296	3742.8
9	106.8	41	512.8	73	919.0	105	1322.8	137	1728.8	169	2135.0	201	2538.8	233	2944.8	265	3351.0	297	3754.8
10	121.0	42	524.8	74	930.8	106	1337.0	138	1740.8	170	2146.8	202	2553.0	234	2956.8	266	3362.8	298	3769.0
11	132.8	43	539.0	75	942.8	107	1348.8	139	1755.0	171	2158.8	203	2564.8	235	2971.0	267	3374.8	299	3780.8
12	144.8	44	550.8	76	957.0	108	1360.8	140	1766.8	172	2173.0	204	2576.8	236	2982.8	268	3389.0	300	3792.8
13	159.0	45	562.8	77	968.8	109	1375.0	141	1778.8	173	2184.8	205	2591.0	237	2994.8	269	3400.8	301	3807.0
14	170.8	46	577.0	78	980.8	110	1386.8	142	1793.0	174	2196.8	206	2602.8	238	3009.0	270	3412.8	302	3818.8
15	182.8	47	588.8	79	995.0	111	1398.8	143	1804.8	175	2211.0	207	2614.8	239	3020.8	271	3427.0	303	3830.8
16	197.0	48	600.8	80	1006.8	112	1413.0	144	1816.8	176	2222.8	208	2629.0	240	3032.8	272	3438.8	304	3845.0
17	208.8	49	615.0	81	1018.8	113	1424.8	145	1831.0	177	2234.8	209	2640.8	241	3047.0	273	3450.8	305	3856.8
18	220.8	50	626.8	82	1033.0	114	1436.8	146	1842.8	178	2249.0	210	2652.8	242	3058.8	274	3465.0	306	3868.8
19	235.0	51	638.8	83	1044.8	115	1451.0	147	1854.8	179	2260.8	211	2667.0	243	3070.8	275	3476.8	307	3883.0
20	246.8	52	653.0	84	1056.8	116	1462.8	148	1869.0	180	2272.8	212	2678.8	244	3085.0	276	3488.8	308	3894.8
21	258.8	53	664.8	85	1071.0	117	1474.8	149	1880.8	181	2287.0	213	2690.8	245	3096.8	277	3503.0	309	3906.8
22	273.0	54	676.8	86	1082.8	118	1489.0	150	1892.8	182	2298.8	214	2705.0	246	3108.8	278	3514.8	310	3921.0
23	284.8	55	691.0	87	1094.8	119	1500.8	151	1907.0	183	2310.8	215	2716.8	247	3123.0	279	3526.8	311	3932.8
24	296.8	56	702.8	88	1109.0	120	1512.8	152	1918.8	184	2325.0	216	2728.8	248	3134.8	280	3541.0	312	3944.8
25	311.0	57	714.8	89	1120.8	121	1527.0	153	1930.8	185	2336.8	217	2743.0	249	3146.8	281	3552.8	313	3959.0
26	322.8	58	729.0	90	1132.8	122	1538.8	154	1945.0	186	2348.8	218	2754.8	250	3161.0	282	3564.8	314	3970.8
27	334.8	59	740.8	91	1147.0	123	1550.8	155	1956.8	187	2363.0	219	2766.8	251	3172.8	283	3579.0	315	3982.8
28	349.0	60	752.8	92	1158.8	124	1565.0	156	1968.8	188	2374.8	220	2781.0	252	3184.8	284	3590.8	316	3997.0
29	360.8	61	767.0	93	1170.8	125	1576.8	157	1983.0	189	2386.8	221	2792.8	253	3199.0	285	3602.8	317	4008.8
30	372.8	62	778.8	94	1185.0	126	1588.8	158	1994.8	190	2401.0	222	2804.8	254	3210.8	286	3617.0	318	4020.8
31	387.0	63	790.8	95	1196.8	127	1603.0	159	2006.8	191	2412.8	223	2819.0	255	3222.8	287	3628.8	319	4035.0
32	398.8	64	805.0	96	1208.8	128	1614.8	160	2021.0	192	2424.8	224	2830.8	256	3237.0	288	3640.8	320	4046.8
33	410.8	65	816.8	97	1223.0	129	1626.8	161	2032.8	193	2439.0	225	2842.8	257	3248.8	289	3655.0		

Note: The figures are indicative or an estimate only. This is a guide and an allowance for manufacturing tolerances (page 70) should be made.

### **GratEX® Rectangular Mesh** 25 x 100 Mesh Grid Load Bar Chart

No.of Bars	mm				(Lengt	h)			
2	106.4	10	906.4	18	1706.4	26	2506.4	34	3306.4
3	206.4	11	1006.4	19	1806.4	27	2606.4	35	3406.4
4	306.4	12	1106.4	20	1906.4	28	2706.4	36	3506.4
5	406.4	13	1206.4	21	2006.4	29	2806.4	37	3606.4
6	506.4	14	1306.4	22	2106.4	30	2906.4	38	3706.4
7	606.4	15	1406.4	23	2206.4	31	3006.4	39	3806.4
8	706.4	16	1506.4	24	2306.4	32	3106.4	40	3906.4
9	806.4	17	1606.4	25	2406.4	33	3206.4	41	4006.4

No.of Bars	mm				(Width)				
2	31.4	10	231.4	18	431.4	26	631.4	34	831.4
3	56.4	11	256.4	19	456.4	27	656.4	35	856.4
4	81.4	12	281.4	20	481.4	28	681.4	36	881.4
5	106.4	13	306.4	21	506.4	29	706.4	37	906.4
6	131.4	14	331.4	22	531.4	30	731.4	38	931.4
7	156.4	15	356.4	23	556.4	31	756.4	39	956.4
8	181.4	16	381.4	24	581.4	32	781.4	40	981.4
9	206.4	17	406.4	25	606.4	33	806.4	41	1006.4

### **GratEX® Rectangular Mesh**

#### 25 x 152 Mesh Grid Load Bar Chart

No. of Bars	mm				(Length	)				No. of Bars	mm				(Width)				
2	158.4	10	1374.4	18	2590.4	26	3806.4	34	5022.4	2	31.4	10	231.4	18	431.4	26	631.4	34	831.4
3	310.4	11	1526.4	19	2742.4	27	3958.4	35	5174.4	3	56.4	11	256.4	19	456.4	27	656.4	35	856.4
4	462.4	12	1678.4	20	2894.4	28	4110.4	36	5326.4	4	81.4	12	281.4	20	481.4	28	681.4	36	881.4
5	614.4	13	1830.4	21	3046.4	29	4262.4	37	5478.4	5	106.4	13	306.4	21	506.4	29	706.4	37	906.4
6	766.4	14	1982.4	22	3198.4	30	4414.4	38	5630.4	6	131.4	14	331.4	22	531.4	30	731.4	38	931.4
7	918.4	15	2134.4	23	3350.4	31	4566.4	39	5782.4	7	156.4	15	356.4	23	556.4	31	756.4	39	956.4
8	1070.4	16	2286.4	24	3502.4	32	4718.4	40	5934.4	8	181.4	16	381.4	24	581.4	32	781.4	40	981.4
9	1222.4	17	2438.4	25	3654.4	33	4870.4	41	6086.4	9	206.4	17	406.4	25	606.4	33	806.4	41	1006.4

Note: The figures are indicative or an estimate only. This is a guide and an allowance for manufacturing tolerances (page 70) should be made.

#### 38 x 100 Mesh Grid Load Bar Chart

No. of Bars	mm				(Length)	)				No. of Bars	mm				(Width)				
2	106.4	7	606.4	12	1106.4	17	1606.4	22	2106.4	2	44.4	7	234.4	12	424.4	17	614.4	22	804.4
3	206.4	8	706.4	13	1206.4	18	1706.4	23	2206.4	3	82.4	8	272.4	13	462.4	18	652.4	23	842.4
4	306.4	9	806.4	14	1306.4	19	1806.4	24	2306.4	4	120.4	9	310.4	14	500.4	19	690.4	24	880.4
5	406.4	10	906.4	15	1406.4	20	1906.4	25	2406.4	5	158.4	10	348.4	15	538.4	20	728.4	25	918.4
6	506.4	11	1006.4	16	1506.4	21	2006.4	26	2506.4	6	196.4	11	386.4	16	576.4	21	766.4	26	956.4

Note: The figures are indicative or an estimate only. This is a guide and an allowance for manufacturing tolerances (page 70) should be made.

#### 60 x 220 Mesh Grid Load Bar Chart

No. of Bars	mm				(Length)	)				N E	No. of Bars	mm				(Width)				
2	226.4	8	1546.4	14	2866.4	20	4186.4	26	5506.4		2	66.4	8	426.4	14	786.4	20	1146.4	26	1506.4
3	446.4	9	1766.4	15	3086.4	21	4406.4	27	5726.4		3	126.4	9	486.4	15	846.4	21	1206.4	27	1566.4
4	666.4	10	1986.4	16	3306.4	22	4626.4	28	5946.4		4	186.4	10	546.4	16	906.4	22	1266.4	28	1626.4
5	886.4	11	2206.4	17	3526.4	23	4846.4	29	6166.4		5	246.4	11	606.4	17	966.4	23	1326.4	29	1686.4
6	1106.4	12	2426.4	18	3746.4	24	5066.4	30	6386.4		6	306.4	12	666.4	18	1026.4	24	1386.4	30	1746.4
7	1326.4	13	2646.4	19	3966.4	25	5286.4	31	6606.4		7	366.4	13	726.4	19	1086.4	25	1446.4	31	1806.4

Note: The figures are indicative or an estimate only. This is a guide and an allowance for manufacturing tolerances (page 70) should be made.

### **Benefits of FRP**



#### **Design Flexibility**

The unique capabilities of conforming partial functionality to the use or application, ease to manufacture and to personalise shapes and aesthetics are just some of the key benefits that draw designers, engineers and architects to composite materials.



#### **Competitive Vs Traditional Materials**

FRP is manufactured from a more economically sound raw material base than metallic alternatives, and is far more structurally sound when compared to timber and plastic materials.

### MoultrEX® Moultruded Fibreglass Grating

# What is MoultrEX° Moultruded Fibreglass Grating

Treadwell's MoultrEX® fibreglass moultruded grating is the first open mesh grating ever to combine the high performance values of fibreglass reinforced plastic (FRP) moulded grating with the amazing capabilities of pultrusion. This has been achieved through clever utilisation of pultrusions within the body of the products' load bars and boasts greater amounts of glass in every item than have ever been seen previously. With the introduction of this revolutionary product, a new vista of grating products is now available to meet both the needs and demands of pedestrian and industrial applications.

Engineered to be lighter than metallic alternatives, MoultrEX® is Treadwell's remarkable hybrid of GratEX®'s moulded and GridEX® pultruded systems. It offers excellent load bearing and resilience characteristics, whilst upholding the highest level of resistance to the elements and corrosives.

The product is also aesthetically pleasing and ideally suited to use in public areas where both smaller apertures ensure compliance with relevant codes, and where requirements for a higher level of finish are called for.



#### MoultrEX® Features and Benefits vs. Traditional Alternatives

	MoultrEX®	Stainless Steel	Galvanised Steel	Aluminium	Polyurethane
Chemical Resistance	••••	••••	•	• • •	• • • •
Strength	• • • •	••••	• • • •	• • • •	• • •
Lightweight	••••	•	•	••••	•••
Electrical Resistance	• • • •	•	•	• • • •	• • • •

#### **MoultrEX® Surface Options**

### Anti-Slip Surface (Standard).

This surface is most commonly used in industrial applications. It is very hard-wearing and has an extremely effective coefficient of friction (NATA laboratory test report available). Unlike serrated steel grating, the anti-slip surface does not impact on load carrying capacity.




#### **Concave Surface**

This is the preferred surface for environments where by-products are commonly caught by serrations, and is hence very often utilised in the food industry. This surface option can also be utilised for guarding options to allow safe handling/contact.



# **MoultrEX® Moultruded Fibreglass Grating**



#### Safe Load & Deflection Charts (mm) - Uniform and Concentrated Line Loads

Span	Unifo	orm load	– ΔU (k	(N/m²) –	- Deflect	ion (mm	n) Co	oncentra	ated line	load –	ΔC (kN/ı	n) – Dei	flection	(mm)
	3 5 8 10 13 15 20 25 30 50 80 90 100 15												150	
38MM UNIFORM LOAD/CONCENTRATED LOAD														

38MN	M UNIFO	RM LOA	D/CONG	CENTRAT	ED LOA	D									
4.00	ΔU	0.086	0.153	0.236	0.276	0.436	0.525	0.657	0.807	1.19	1.656	2.717	3.141	3.52	6.112
400	ΔC	0.268	0.636	1.171	1.355	1.632	1.816	2.276	2.737	3.198	5.04	7.803	8.725	9.646	
600	ΔU	0.246	0.53	0.849	1.038	1.198	1.337	1.868	2.387	2.865	4.774	7.639	8.594	9.549	
600	ΔC	0.782	1.249	1.95	2.437	3.168	3.656	4.875	6.093	7.312					
800	ΔU	0.983	1.597	2.632	3.321	3.719	5.028	6.62	8.211	9.803					
800	ΔC	2.343	3.79	6.14	7.707	10.057									
1000	ΔU	2.461	4.233	6.62	8.234										
1000	ΔC	3.656	6.147	10.065											
1200	ΔU	4.16	7.15												
1200	ΔC	5.491	9.321												
1400	ΔU	6.62													
1400	ΔC	8.82													
1600	ΔU	9.803													
1600	ΔC														

50MN	1 UNIFO	RM LOA	.D/CONC	ENTRAT	ED LOA	D									
400	ΔU	0.054	0.152	0.184	0.154	0.239	0.271	0.403	0.534	0.659	1.136	1.557	1.837	2.539	3.171
400	ΔC	0.203	0.308	0.566	0.73	0.976	1.129	1.416	1.741	2.089	3.482	5.571	6.964	10.446	
(00	ΔU	0.068	0.104	0.19	0.265	0.324	0.424	0.5	0.68	1.058	1.276	1.54	2.6	3.8	7.8
600	ΔC	0.312	0.562	0.86	1.139	1.557	1.821	2.343	2.974	3.67	6.456	10.634			
800	ΔU	0.211	0.35	0.606	0.78	0.98	1.08	1.476	1.86	2.26	3.806	6.1	7.7		
800	ΔC	1.129	1.741	2.785	3.482	4.526	5.223	6.964	8.705	10.446					
1000	ΔU	0.976	1.845	2.8	3.459	4.573	5.316	7.173	9.03	10.886					
1000	ΔC	1.567	2.611	4.178	5.223	6.79	7.834	10.446							
1200	ΔU	1.738	2.935	4.841	6.089	7.84	9.007								
1200	ΔC	3.388	5.531												
1400	ΔU	4.16	7.179	11.726											
1400	ΔC	4.446	7.526												
1600	ΔU	6.366	10.324												
1600	ΔC	5.999	9.829												



## MoultrEX® Installation Methods & Accessories

Treadwell stocks a range of durable 316 stainless steel secure clip options for MoultrEX® moultruded FRP grating. Further details regarding fixing types and ordering information can be found on page 86.


#### Clip - Tops

MoultrEX° M	3D	PLAN	ELEVATION	FASTENING OPTIONS
Hole Diameter: 6mm Material type: 316 st/st Threaded hole: N/A				2

#### **Clamp Underside**

Mini J Universal	G	U	V
	F	2	
Hole Diameter: N/A Material type: 316 st/st Threaded hole: N/A	Hole Diameter: 6mm Material type: st/st Threaded hole: Yes	Hole Diameter: 8mm Material type: 316 st/st Threaded hole: Yes	Hole Diameter: 8mm Material type: 316 st/st Threaded hole: N/A

#### **Fixing Assembly Combinations**



Please refer to Appendix 6b: MoultrEX® Fasteners Ordering Information (Page 86).

# MoultrEX® Moultruded Fibreglass Grating Specification

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### **Ordering Information** Code

- Nominate the type of grating F-MG = GratEX® Moulded Grating required
- Nominate depth (mm) 38 and 50 required
- Nominate the load bar centres  $(25/100) = 25 \text{mm} \times 100 \text{mm}$ required (38/100) = 38mm x 100mm
- Nominate the mesh type required R = Rectangular Mesh

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

- Specify the resin, material or type O = O-Series (see page 6) I = I-Series®
  - V = V-Series®
- Specify the colour required
  - \*In which instance a code and name of Y = Safety Yellow the selected colour must be mentioned LG = Light Grey within the description.
- G = Industrial Green
  - DG = Dark Grey
  - CH = Charcoal C = Custom\*

Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications

Nominate the panel size required  $1 = 1200 \text{ mm} \times 5900 \text{ mm}$ 2 = 920 mm x 3055 mm

Please refer to Appendix 4: MoultrEX® Ordering Codes - page 83

N Non-Stocked Item C Commonly Stocked Item


### **GridEX® Pultruded Fibreglass Grating**

# What is **GridEX**° Pultruded Fibreglass Grating

Treadwell's GridEX® pultruded FRP grating systems are designed for specific applications where a standard fibreglass grating system cannot be effectively be utilised. GridEX® offers you options such as selection of open space, bar shape, cross-rod placement, custom fabrication, and custom resin or colour.

A wide variety of bar shapes along with various bearing bar and cross-rod spacings are available depending on the design requirements. Refer to the safe load and deflection charts for our standard selection, and please do not hesitate to contact us for details relating to our custom options.

Most common GridEX® options are available in 25 mm, 38 mm and 50 mm depths. However, Treadwell brings to the market extremely heavy duty versions of GridEX® that offer more durable, stronger and much larger span capacities as the situation calls for.



### **GridEX® Cross Rod Systems**

Treadwell is the only company to offer numerous cross rod systems, allowing you the flexibility to achieve what is required for your application.





### **GridEX® Surface Options**

#### **Ribbed Surface**

This is the preferred surface for environments where by-products are commonly caught by serrations, and is hence very often utilised in the food industry. This surface option can also be utilised for wet areas and wash down applications.



#### Anti-Slip Surface (Standard)

A very hard-wearing surface with an extremely effective coefficient of friction (NATA laboratory test report available) — commonly used in industrial applications. Unlike serrated steel grating, the anti-slip surface does not impact load carrying capacity.



#### **Covered Surface**

This non-stock option is very often utilised for applications where high strength covered floors are required. The system is supplied with Checkerplate or Anti-Slip surface bonded to every load bar to ensure performance is maintained in harsh environments.



### **GridEX® I Type Grating**








### RailEX® FRP Handrail

The RailEX® FRP handrail system is a patented industrial rated product that is noted for its durability, strength, and versatility. Further, Treadwell's FRP handrail system has multiple uses in many industries and markets, and can be tailored to meet the requirements of our clients. Treadwell can deliver RailEX® as components or as prefabricated systems for immediate installation.

Treadwell's FRP handrails are available both in square and round configurations.



## **GridEX® I Type Grating**



# **GridEX® I Type Grating**

### Safe Load & Deflection Charts (mm) - Uniform and Concentrated Line Loads

	Grid		C ~		Unifor	m load	– ΔU (k	N/m²) -	- Deflec	tion (m	m) Con	centrat	ed line	load – 1	۷C (kN/ı	m) – De	eflectior	n (mm)	Safe Load
Open	Closed	Depth	) Sh	an	3	5	8	10	13	15	20	25	39	50	100	150	200	250	kN
E DC	25(7.8/5	2)1	_																
F-PG	25(7.6/3	0.5)1		ΔU	0.1	0.2	0.3	0.3	0.4	0.5	0.6	0.8	1.2	1.6	3.2	4.8	6.4	8.0	298
			400	ΔC	0.1	0.2	1.0	1.3	1.7	1.9	2.6	3.2	5.0	6.4	12.8	4.0	0.4	6.0	59
				ΔU	0.4	0.7	1.0	1.3	1.7	2.0	2.6	3.3	5.1	6.6	13.1				143
			600	ΔC	1.0	1.7	2.8	3.5	4.5	5.2	7.0	8.7	13.6	0.0					43
		25		ΔU	1.2	1.9	3.1	3.9	5.0	5.8	7.7	9.6	15.1						82
60%	40%	mm	800	ΔC	2.3	3.9	6.2	7.7	10.0	11.6	15.4								33
			1000	ΔU	2.8	4.6	7.3	9.2	11.9	13.8									53
			1000	ΔC	4.4	7.3	11.7	14.7											26
			1200	ΔU	5.6	9.3	14.9												35
			1200	ΔC	7.5	12.4													22
F-PG	25(7.8/7	7.8)I																	
			400	ΔU	0.1	0.1	0.2	0.2	0.3	0.3	0.4	0.5	0.8	1.1	2.1	3.2	4.3	5.3	446
			400	ΔC	0.3	0.4	0.7	0.9	1.1	1.3	1.7	2.1	3.3	4.3	8.5	12.8			89
			600	ΔU	0.3	0.4	0.7	0.9	1.1	1.3	1.8	2.2	3.4	4.4	8.8	13.1			214
			000	ΔC	0.7	1.2	1.9	2.3	3.0	3.5	4.7	5.8	9.1	11.7					65
40%	60%	25	800	ΔU	0.8	1.3	2.1	2.6	3.4	3.9	5.2	6.4	10.1	12.9					124
10,0		mm		ΔC	1.5	2.6	4.1	5.2	6.7	7.7	10.3	12.9							49
			1000	ΔU	1.8	3.1	4.9	6.1	8.0	9.2	12.3	15.3							79
				ΔC	2.9	4.9	7.8	9.8	12.7	14.7									39
			1200	ΔU	3.7	6.2	9.9	12.4											53
				ΔC	5.0	8.3	13.3												32
F-PG	38(15/2	22.8)I																	
			400	ΔU	0.02	0.04	0.07	0.08	0.09	0.11	0.13	0.18	0.22	0.31	0.62	0.93	1.25	1.56	504
			700	ΔC	0.2	0.3	0.5	0.6	0.7	0.8	1.1	1.4	2.2	2.8	5.6	8.4	11.3	14.1	100
			600	ΔU	0.09	0.13	0.18	0.22	0.31	0.36	0.44	0.58	0.89	1.16	2.31	3.47	4.62	5.78	217
				ΔC	0.4	0.7	1.1	1.4	1.8	2.1	2.8	3.5	5.4	7.0	13.9				66
			800	ΔU	0.18	0.31	0.53	0.67	0.84	0.98	1.29	1.65	2.53	3.29	6.54				124
		20		ΔC	0.9	1.5 0.76	2.4 1.20	2.9 1.51	3.8 1.96	4.4 2.27	5.9 3.02	7.4 3.82	11.5 5.91	14.7					78
60%	40%	38 mm	1000	ΔC	1.6	2.7	4.4	5.5	7.1	8.2	10.9	13.7	3.91						38
				ΔU	0.93	1.56	2.49	3.11	4.05	4.67	6.23	13.7							50
			1200	ΔC	2.8	4.7	7.5	9.3	12.1	14.0	0.23								30
				ΔU	1.73	2.89	4.62	5.74											36
			1400	ΔC	4.4	7.4	11.8	14.8											25
			1600	ΔU	0.00	2.93	4.89												27
			1600	ΔC	6.6	11.0													21
F-PG	38(7.8/7	7.8)																	
				ΔU	0.0	0.0	0.1	0.1	0.1	0.1	0.2	0.2	0.4	0.5	0.9	1.4	1.9	2.3	756
			400	ΔC	0.1	0.2	0.3	0.4	0.5	0.6	0.8	0.9	1.5	1.9	3.8	5.6	7.5	9.4	150
			(00	ΔU	0.1	0.2	0.3	0.3	0.5	0.5	0.7	0.9	1.4	1.7	3.5	5.2	7.0	8.7	325
			600	ΔC	0.3	0.5	0.7	0.9	1.2	1.4	1.9	2.3	3.6	4.6	9.3	13.9			99
			800	ΔU	0.3	0.5	0.8	1.0	1.3	1.5	2.0	2.5	3.8	4.9	9.8	14.7			185
			300	ΔC	0.6	1.0	1.6	2.0	2.6	2.9	3.9	4.9	7.7	9.8					74
40%	60%	38	1000	ΔU	0.7	1.1	1.8	2.3	3.0	3.4	4.6	5.7	8.9	11.4					116
1070	5070	mm		ΔC	1.1	1.8	2.9	3.7	4.7	5.5	7.3	9.1	14.2						58
			1200	ΔU	1.4	2.3	3.7	4.7	6.1	7.0	9.3	11.7							75
				ΔC	1.9	3.1	5.0	6.2	8.1	9.3	12.5	15.6							45
			1400	ΔU	2.6	4.3	6.9	8.6	11.2	13.0									55
				ΔC	3.0	4.9	7.9	9.9	12.8	14.8									38
			1600	ΔU	4.4	7.3 7.3	11.7 11.7	14.7 14.7											32
				ДС	4.4	1.)	11./	14./											



### **GridEX® I Type Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- 3.1 The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- 6.1 All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- 7.1 All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- 7.2 Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- 7.7 All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- 7.8 Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- 7.9 The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- 7.11 Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### Ordering Information

#### Code

- Nominate the type of grating F-MG = GratEX® Moulded Grating required
- Nominate the depth (mm) 25, 38 and 76 required
- Nominate the load bar centres  $(5.3/7.8) = 5.3 \text{mm} \times 7.8 \text{mm}$ required  $(7.8/5.3) = 7.8 \text{mm} \times 5.3 \text{mm}$  $(7.8/7.8) = 7.8 \text{mm} \times 7.8 \text{mm}$  $(7.8/12) = 7.8 \text{mm} \times 12 \text{mm}$  $(15/10) = 15 \text{mm} \times 10 \text{mm}$  $(15/15) = 15 \text{mm} \times 15 \text{mm}$  $(15/22.8) = 15 \text{mm} \times 22.8 \text{mm}$
- 4. Nominate the mesh type required I = I Type

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

- 5. Specify the resin, material or type O = O-Series® V = V-Series®
- 6. Specify the colour required

  \*In which instance a code and name of
  the selected colour must be mentioned
  within the description.

G = Industrial Green
Y = Safety Yellow
LG = Light Grey
DG = Dark Grey
CH = Charcoal

C = Custom\*

7. Specify the surface style required

CG = Commercial Grade (Grit) Anti-Slip G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip CH = Chequer Plate


 $\label{eq:Palain(Flat)} P = Plain(Flat)$  Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications.

8. Nominate the panel size required  $1 = 1225 \text{ mm} \times 3665 \text{ mm}$  $2 = 920 \text{ mm} \times 3055 \text{ mm}$ 

Please refer to Appendix 5: GridEX® Ordering Codes - page 84

N Non-Stocked Item C Commonly Stocked Item

### **GridEX® T Type Grating**





### **ArchitEX™ FRP Structural Profiles**

The Treadwell team is delighted to introduce ArchitEX<sup>TM</sup>, our structural range of FRP profiles. Serving as the ultimate tool for designing FRP structures, the data in this structural product guide has been collated to ensure that engineers and architects have the ideal reference available to them while designing structures for highly corrosive applications.

Treadwell has also made data from the guide available through our TreadSpec® online selection tool, which allows users to fill in selection criteria in order to obtain relevant load & deflection information making for simpler and easier design of FRP structures.





# **GridEX® T Type Grating**

### Safe Load & Deflection Charts (mm) - Uniform and Concentrated Line Loads

	Grid				Unifor	m load ·	– ΔU (k1	N/m²) –	Deflect	ion (mn	n) Co	ncentra	ted line	load –	ΔC (kN,	/m) – D	eflectio	n (mm)
Depth	Closed	Open	Sp	an	3	5	8	10	13	15	20	25	39	50	100	150	200	250
E D.C.	-0/25/45	) <del>-</del> ) <del>-</del>																
F-PG5	50(25/12 I	2./)																
			400	ΔU	0.0	0.1	0.1	0.1	0.1	0.2	0.2	0.3	0.4	0.5	1.0	1.6	2.1	2.6
				ΔC	0.1	0.2	0.3	0.4	0.5	0.6	0.8	1.0	1.6	2.1	4.1	6.2	8.3	10.3
			600	ΔU	0.1	0.2	0.3	0.3	0.4	0.5	0.7	0.9	1.3	1.7	3.4	5.2	6.9	8.6
				ΔC	0.3	0.5	0.7	0.9	1.2	1.4	1.8	2.3	3.6	4.6	9.2	13.8		
			800	ΔU	0.3	0.5	0.7	0.9	1.2	1.4	1.8	2.3	3.6	4.5	9.0	13.6		
				ΔC	0.5	0.9	1.4	1.8	2.4	2.7	3.6	4.5	7.1	9.0				
50%	50%	50	1000	ΔU	0.6	1.0	1.7	2.1	2.7	3.1	4.2	5.2	8.1	10.4				
50%	50%	mm	1000	ΔC	1.0	1.7	2.7	3.3	4.3	5.0	6.6	8.3	13.0					
			1200	ΔU	1.2	2.1	3.3	4.1	5.4	6.2	8.3	10.3						
			1200	ΔC	1.7	2.8	4.4	5.5	7.2	8.3	11.0	13.8						
				ΔU	2.2	3.7	6.0	7.4	9.7	11.2	14.9							
			1400	ΔC	2.6	4.3	6.8	8.5	11.1	12.8								
				ΔU	3.8	6.3	10.1	12.6										
		1600	ΔC	3.8	6.3	10.1	12.6											
	I	l			3.0													
F-PG5	50(25/25	5)T																
			400	ΔU	0.0	0.1	0.1	0.1	0.1	0.2	0.2	0.3	0.4	0.5	1.0	1.6	2.1	2.6
			400	ΔC	0.1	0.2	0.3	0.4	0.5	0.8	0.8	1.0	1.6	2.1	4.1	6.2	8.3	10.3
			(00	ΔU	0.1	0.2	0.3	0.3	0.4	0.5	0.7	0.9	1.3	1.7	3.4	5.2	6.9	8.6
			600	ΔC	0.3	0.5	0.7	0.9	1.2	1.4	1.8	2.3	3.6	4.6	9.2	13.8		
				ΔU	0.3	0.5	0.7	0.9	1.2	1.4	1.8	2.3	3.6	4.5	9.0	13.6		
			800	ΔC	0.5	0.9	1.4	1.8	2.4	2.7	3.6	4.5	7.1	9.0				
		50		ΔU	0.6	1.0	1.7	2.1	2.7	3.1	4.2	5.2	8.1	10.4				
33%	66%	mm	1000	ΔC	1.0	1.7	2.7	3.3	4.3	5.0	6.6	8.3	13.0					
				ΔU	1.2	2.1	3.3	4.1	5.4	6.2	8.3	10.3						
			1200	ΔC	1.7	2.8	4.4	5.5	7.2	8.3	11.0	13.8						
				ΔU	2.2	3.7	6.0	7.4	9.7	11.2	14.9	15.0						
			1400	ΔC	2.6	4.3	6.8	8.5	11.1	12.8	14.7							
				ΔU	3.8	6.3	10.1	12.6	11.1	12.0								
			1600	ΔC														
				ΔC	3.8	6.3	10.1	12.6										

### **GridEX® T Type Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- 3.1 The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

Ordering	Information	Code
Olueliiig	IIIIOIIIIauoii	Cou

1.	Nominate	the	type	of	grating	F-PG = GridEX® Pultruded
	required					Grating

- Nominate the depth (mm) 25, 38 and 50 required
  - Nominate the load bar centres  $(22/25) = 22mm \times 25mm$ required (25/5) = 25 mm x 5 mm(25/12.7) = 25mm x 12.7mm (40/9.6) = 40mm x 9.6mm (40/22.3) = 40mm x 22.3mm
- Nominate the mesh type required T = T Type

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

Specify the resin, material or type	O = O-Series®
(see page 6)	I = I-Series®
	V = V-Series®

Specify the colour required \*In which instance a code and name of Y = Safety Yellowthe selected colour must be mentioned LG = Light Greywithin the description.

G = Industrial Green DG = Dark Grey CH = Charcoal C = Custom\*

Specify the surface style required

CG = Commercial Grade (Grit) G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip CH = Chequer Plate P = Plain(Flat)

Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications.


Nominate the panel size required 1 = 1200 mm x 5900 mm 2 = 920 mm x 3055 mm


Please refer to Appendix 5: GridEX® Ordering Codes - page 84

N Non-Stocked Item C Commonly Stocked Item



### **GridEX® Bar Type Grating**









### SAFE-SERIES™ Anti-Slip Products

SAFE-SERIES™ is Treadwell's selection of pre-manufactured and ready made for installation anti-slip products for harsh environments. Fabricated from FRP composites, anti-slip stair nosings, deck plating and rung covers are easy to install over existing stairs to create the toughest and most dependable anti-slip surface available.

The SAFE-SERIES™ product range offers a wide range of anti-slip solutions which can be used in numerous applications (proven in many applications). The series is available in various styles and colours to suit any environment.

### **GridEX® Bar Type Specification**

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 ASTM E84 Surface Burning Characteristics of Building Materials
  - 2.1.2 ASTM D635 Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.

#### 3.0 Design Criteria

- The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- Contact Treadwell regarding specification data relative to products conforming to ASTM D635.

- All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex Stainless Steel, hot dipped galvanised steel or aluminium.
- Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### **Ordering Information**

#### Code

- Nominate the type of grating  $F-PG = GridEX^{\circ} Pultruded$ required Grating
- Nominate the depth (mm) 25, 38, 50 and 64 required
  - Nominate the load bar centres  $(15/10) = 15 \text{mm} \times 10 \text{mm}$ required (15/15) = 15mm x 15mm (15/23) = 15mm x 23mm
- Nominate the mesh type required B = Bar Type

Note: This section of the coding is typically separated from the next section of the coding by a dash (-)

- Specify the resin, material or type O = O-Series
  - (see page 6) I = I-Series® V = V-Series®
- Specify the colour required
  - G = Industrial Green \*In which instance a code and name of Y = Safety Yellow the selected colour must be mentioned LG = Light Grey within the description. DG = Dark Grey CH = Charcoal
- Specify the surface style required

CG = Commercial Grade (Grit) Anti-Slip G = Industrial Grade (Grit) Anti-Slip MG = Marine Grade (Grit) Anti-Slip CH = Chequer Plate P = Plain(Flat)

C = Custom\*


Note: The next section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications.

Nominate the panel size required  $1 = 1200 \text{ mm} \times 5900 \text{ mm}$ 2 = 920 mm x 3055 mm

Please refer to Appendix 5: GridEX® Ordering Codes - page 84

N Non-Stocked Item C Commonly Stocked Item

### **GridEX® Stair Treads and Landings**



Treadwell's range of GridEX® Stair Treads includes both open surface and closed surface options, with a range of surface patterns, colour and leading edge nosing options.

GridEX® Stair Treads are normally implemented in applications where there are greater load bearing and strength capacities required that other grating variations cannot offer. The GridEX® Treads are available in all bar types and dimensional variations.


All GridEX® Premium and Standard Stair Tread options are moulded with the Solid Leading Edge Nosing as an integrated single stage operation. This increases the rigidity and durability of the entire leading edge, ensuring reliable performance in high traffic scenarios. All the treads with abrasive leading edge nosings are manufactured to conform with AS 1657 – 2018.

The GridEX® Stair Tread nosings (premium treads only) are typically stocked in colours that contrast by 30% with the primary tread colour. This ensures maximum visual awareness of the stair treads forward edge for operators utilising the stairways and consequently enhancing the OHS safety ratings.

Treadwell recommends that leading edge nosings are specified when ordering  $GridEX^{\odot}$  Stair Treads as the safety risks associated with elevated work areas or walkways is significantly increased without them.

**NOTE**: A bearing surface of at least 40mm is recommended at either side of GridEX® Stair Treads. Compliance with AS 1657 – 2018 requires a tread depth of less than 225mm.

Selecting a tread with lasting non-slip properties, resilience to corrosion and proven long term cost advantages can help you enhance safety in the workplace by reducing the chance of slips, trips and falls.



#### **Benefits of FRP**



GridEX® Square Mesh

#### **Virtually Maintenance Free**

Given the nature of FRP, any system utilising it is virtually maintenance free, thus keeping maintenance costs as low as possible.

### **GridEX® Installation Methods & Accessories**

Treadwell stocks a range of durable 316 stainless steel secure clip options for GridEX® pultruded FRP grating. Further details regarding fixing types and ordering information can be found on page 87.

For apertures between each load bar which are less than 15mm, the  $GridEX^{\otimes}$  M clip with the 6mm hole diameter is recommended. For 15mm and above, the  $GridEX^{\otimes}$  M clip with the 8mm hole diameter is recommended.


#### Clip - Tops

ITEM	PROFILES	HOLE DIAMETER	MATERIAL TYPE	THREADED HOLE	FASTENING OPTIONS
GridEX <sup>®</sup> M		Hole diameter is dependent on load bar and aperture sizes.	316 st/st	N/A	2

#### **Clamp Underside**

Mini J Universal	G	U	V
	F	2	
Hole Diameter: N/A Material type: 316 st/st Threaded hole: N/A	Hole Diameter: 6mm Material type: st/st Threaded hole: Yes	Hole Diameter: 8mm Material type: 316 st/st Threaded hole: Yes	Hole Diameter: 8mm Material type: 316 st/st Threaded hole: N/A

#### **Fixing Assembly Combinations**



Please refer to Appendix 6c: GridEX® Fasteners Ordering Information (Page 87).

### P-Series® Phenolic Grating



grating is the ultimate choice for applications where fire risk is prevalent and when smoke cannot be allowed to develop.

Treadwell, through the employment of the most advanced production equipment and the use of the highest quality raw materials, has developed this unique range of leading offshore composite grating products. EX-Series® Phenolic Grating, which boasts US Coast Guard approval, is acceptable for use in areas and applications as outlined in the US Coast Guard Safety Manual Vol III.

#### Composite Grating with the Strength of Steel

EX-Series® Phenolic Grating can span up to 70% more than that of equivalent size standard steel grating. Furthermore, P-Series® will not yield and will return to its original shape if design loads are exceeded.

#### Ease of Installation

EX-Series® Phenolic Grating is only 65% of the weight of steel bar grating and often, can be manually installed with ease.

#### Safety Enhancing Anti-Slip Surface

This system unique to EX-Series® Grating Systems means that load bars are broader than those of metal grating and are far less fatiguing than conventional steel bar grating and not dangerously sharp like serrated surface grating.

#### **Standard Colours**



### Extreme Fire and Impact Resistance

EX-Series® Phenolic Grating systems, which is laminated by an outer layer of resin rich Phenolic providing ultimate fire resistance, ensures extreme strength is maintained.

#### **Typical Applications**

- Jetties, wharfs & marine structures Refineries
- Offshore production platforms
- Offshore drilling platforms
- Grating

- Industrial/processing plants
- Shipboard applications
- Public Transport i.e. tunnels

#### Standard Panel Sizes

**GratEX®** 1225 mm x 3665 mm 920 mm x 3055 mm

GridEX® 1524 mm x 6096 mm

Other custom panels sizes are achievable and readily available.

#### **Installation Methods**

Treadwell offers a range of Installation fixing systems designed for offshore wave zone environments as well as for standard industrial applications – refer to pages 38-41, 50, 68 and 80 for StormChief® system, which has a long-standing history of outstanding performance in the offshore industry.



### P-Series® Phenolic Grating Specification

#### General

#### 1.0 Scope

1.1 The grating shall conform to the material and fabrication requirements as per this specification.

#### 2.0 Standards/Related documents

- 2.1 The grating system shall conform to the applicable sections of:
  - 2.1.1 US coast guard approvals, level 2 and 3

#### 3.0 Design Criteria

- 3.1 The design criteria of the fibreglass products (FRP) shall be in accordance with governing building codes and generally accepted standards in the FRP industry.
- 3.2 Design live loads shall be of ... kPa uniformly distributed load (or as per building code if more stringent) with a maximum deflection of ... mm at the centre of a single span according to product specifications.

#### 4.0 Submittals

- 4.1 Shop drawings of all fabricated grating panels shall be submitted by Treadwell (unless provided by the client) displaying clearly material sizes, types, styles, product codes and including types and sizes of fasteners as well as a layout if required.
- 4.2 Technical data and sample pieces can also be submitted if required.

#### 5.0 Quality Assurance

Quality surrounds every aspect of Treadwell's commitment to our superior products and efficiency. Treadwell's quality assurance strictly adheres to the high quality control standards placed to conform to relevant specifications, codes, Australian Standards and contractual requirements in a timely manner.

#### 6.0 Product Delivery and Storage

- 6.1 All grating and components or ancillary items shall be fabricated as per the design and piece marked to design drawings.
- 6.2 All manufactured materials shall be delivered in unbroken packages.

#### **Product System**

#### 7.0 Manufacturing Process

- 7.1 All fibreglass (FRP) items listed under this section shall be constructed from fibreglass reinforcement and resin of the quality necessary to meet the design requirements and dimensions as specified.
- 7.2 Fibreglass reinforcement shall be continuous roving and shall be in sufficient quantities as required for the application.
- 7.3 Resins shall be ... (refer to page 5) with chemical formulations as necessary to provide the corrosion resistance, strength and any other physical properties as required.
- 7.4 All finished surfaces to be smooth, resin-rich, free of voids and without dry spots, cracks or unreinforced areas and all fibreglass reinforcement shall be well covered with resin to protect against exposure due to weather or wear.
- 7.5 All fibreglass (FRP) items shall be EITHER non-fire retardant OR have a tested flame spread rating of 25 or less when tested in accordance with the ASTM E84 Tunnel Test.
- 7.6 Contact Treadwell regarding specification data relative to products conforming to ASTM D635.
- 7.7 All metal accessories shall be manufactured from (304 or 316) Stainless Steel, 2205 Duplex Stainless Steel, 2507 Super Duplex

Stainless Steel, hot dipped galvanised steel or aluminium.

- 7.8 Load bars shall be joined with notched cross bars via interlocking methods and the use of chemical bonding.
- 7.9 The fibreglass reinforcement content shall be maintained at 65% (by weight) so as to achieve maximum loading capacity.
- 7.10 All fibreglass material shall have an ultraviolet light inhibiting chemical additive to resist UV degradation.
- 7.11 Grating shall be manufactured with a concave profile on top of each bar OR an anti-slip Aluminium Oxide surface to provide optimum slip resistance.

#### 8.0 Acceptable Manufacturer

The fibreglass underfoot moulded grating system shall be manufactured by Treadwell Group Pty Ltd of Australia.

#### **Ordering Information**

### Nominate the type of grating required

#### F-MG = GratEX® Moulded Grating F-PG = GridEX® Pultruded Grating

- 2. Nominate the depth (mm) required
- 3. Nominate the load bar centres that you require

#### t (38/38) = 38mm x 38mm for Square Mesh (7.8/12) = 7.8mm x 12mm for GridEX® I Type

Note: This section of the coding is typically separated from the next section of the coding by a dash  $(\cdot)$ 

4. Nominate the mesh type required | = |

I = I Type S = Square Mesh

- 5. Specify the resin, material or type
- P = P-Series®

Code

25 and 38

Example: F-PG38(15/10)IP

N Non-Stocked Item C Commonly Stocked Item



### **Colour Palette**

#### All Treadwell FRP grating products are available to order with any colour that you may specify.

While we carry one of the broadest offerings of commonly used colours, our FRP grating range offers unlimited flexibility when trying to match to an existing colour scheme. All of the grating types that make up the Treadwell range can be requested in a custom or RAL matched colour.

A selection of colours is offered below. It is important to note that our range is NOT limited to these colours and not all products may be immediately available in the colours listed below.

#### **Standard Colours**



### **Colours & Effects**



#### **Descriptive Markings**

Overhead safety warnings and signage can actually create a slip, trip and fall situation when the person fails to look down while walking. Worse yet, in the event of a fire or emergency, smoke and darkness often conceal overhead signage and directional guidance.

The image or message can be embedded into the cover, not just printed on the surface, so it will last for the life of the product and not wear off.

Treadwell can also incorporate your company logo and other custom graphics into the surface without affecting slip performance.

#### **Glow in the Dark Colours**

Treadwell is also proud to offer innovative glow-in-the-dark products which use an embedded inorganic photo luminescent pigment that creates a green/yellow glow when active. The pigment is non-toxic, non-radioactive, and can be recharged repeatedly during the life of the product.

These products are an effective safety solution for both outdoor and indoor applications, with greater visibility for many hours after the light source has been removed.

The photo luminescent pigment is fully recharged after 5 minutes of exposure to sunlight, 8 minutes at dusk, or 10 minutes in fluo rescent light; depending on the strength and nature of the light source. The higher the UV output, the brighter the illumination.

### **Two-Tone Colour Configurations**

Colours can also be combined to create a two-tone configuration. Contrasting colours can be applied on (but not limited to):

- On the nosing and vertical lip of a step cover, increasing notice to the leading edge of a stair.
- On the perimeter of a walkway cover where a change in surface texture and colour signifies a safe walk zone.
- On RungSAFE® Covers.

In addition, it is an economical alternative to full photo luminescent covers combined with a solid colour. Not only do you have a two-tone configuration in the light, but also the benefit of glow in the dark when the light source is removed.







# **Anti-Slip Grit Grades**

#### **Cover Grit Options**

Every grating surface has Treadwell's unique layer of resin surface with embedded grit that characterises its high traction and safety traits. Depending on application, our range of grit covers can offer the highest anti-slip properties available on the market to smaller grits where specified.

#### **Hardness of Grit**

Treadwell incorporates a unique grit product into all of our antislip products. Measuring at 9.4 on Moh's Hardness Scale, most tapes and paints which contain quartz or silica (in other words, sand) pale in comparison. These score a soft aggregate of 6-7 that will quickly wear away under foot traffic, leaving your surface more open to hazards.

Mohs Hardness Scale	
Diamond	10.0
Fused Alumina	9.4
Quartz Sand Most Anti-Slip Products Including Tapes	6-7



#### **Ten Standards Grades**





## What is HygiGR8®

The Treadwell HygiGR8® range was initially developed to service the food and beverage processing industry with the emphasis on streamlining cleaning processes and addressing hygiene issues in food processing operations.

With product evolution, HygiGR8® is now available as a comprehensive solution when particles being entrapped between support members and grating is a concern.

HygriGR8® incorporates a unique blend of solid top and open grating technology. This is achieved through the calculated layout of HygiGR8® panels to ensure the solid top section of customisable width around the edge of each panel is located so that the beams that make up the substructure are covered by the solid band.

The grating system can be manufactured from any grade of resin for any industry including premium food grade polyester resin.

For HygiGR8® intended for food and beverage processing facilities, Treadwell certifies that food grade resin HygiGR8® meet USDA acceptance requirements when properly installed and maintained as an ergonomic or anti-slip floor surface or cover. Each panel is post cured and detergent washed.

This unique system can be adapted to any floor plan, for uses such as landings, slippery ramps, catwalks, decks etc. HygiGR8® also incorporates treads that can be manufactured to any standard for continuity of HygiGR8® over walkways and stairways.



#### HygiGR8® Features and Benefits vs. Traditional Alternatives

	HygiGR8®	Stainless Steel	Galvanised Steel	Aluminium	Polyurethane
Chemical Resistance	• • • •	• • • •	•	• • •	• • • •
Strength	• • • •	• • • •	• • • •	• • • •	• • •
Lightweight	• • • •	•	•	• • • •	• • •
Electrical Resistance	• • • •	•	•	•	••••
Cleaning	• • • • •	• • •	• • •	• • •	•
Hygiene	• • • •	• • • •	•	• •	• • • •

#### **HygiGR8® Surface Options**

**Anti-Slip Surface.** HygiGR8® is recommended with a gritted antislip surface to ensure maximum grip in situations where there are typically moisture and slippery residues. It has an extremely effective coefficient of friction and is very hard-wearing (NATA laboratory test report available).



**Concave Surface.** HygiGR8® can also be ordered with the concave surface option. This ensures efficient and easier to clean environments where by-products are commonly caught between serrations. However, the anti-slip properties are not as profound as the gritted surface.



### **Residue Build Up Prevention**

### HygiGR8® Clip

The HygiGR8® clip was specifically designed to resolve the issue of residue caught in between the grating and support members, especially in food and mining environments. Together with DeckSAFE®, the HygiGR8® clip formulates a system that safeguards any build up in-between the apertures of the grating panels.

#### **DeckSAFE®**


DeckSAFE® has emerged as one of the market's genuine solutions for landings, slippery ramps, catwalks, decks, etc. It is mainly designed to eliminate the threats of trips, slips as well as falls in the workplace where there is direct contact with water, oil and other forms of liquids to reduce risks.

DeckSAFE® can be applied in customisable strips of up to 3m in length to be utilised in conjunction with the HygriGR8® clip.

#### **Installation Guide**









#### **Fastening Clips**



Screw	3D	PLAN	ELEVATION
Threaded Size: 10mm Material Type: st/st Length: 22mm	The state of the s		

### **Conductive Grating**



# What is EX-Series® Conductive Grating?

FRP gratings are typically non-conductive and this can sometimes present a safety issue when in a sparking sensitive environment due to the build-up of static electricity.

The black carbon surface in Treadwell's conductive grating is specially formulated to discharge static build-up on FRP grating surfaces in areas where static build-up presents a significant risk. When properly grounded, the conductive surface provides solutions that can be typically applied in areas where there is highly sensitive electrical equipment, munitions, chemical or petro chemicals present.

Treadwell's conductive grating drains off the build-up of unwanted, dangerous static electricity when grounded. This specialised grating produces an electrical resistance of less than 26-kilo-ohms per foot, while retaining other desirable characteristics of conventional FRP moulded grating.

The Treadwell moulded carbon top can be applied to any of the grating products specified in our range and can be combined with any of our resin formulations.



#### **Based on NFPA77**

#### **Recommended 4 grounding attachments**


- Average Surface Resistivity 2.5 X 103 ohms to 1 x 106 ohms per lineal foot
- Average Resistance to Ground <108 ohms






### **Terminology**

A section fixed at right angles to the Load Bar designed to provide lateral strength — GridEX® pultruded grating is constructed




#### **Cut Out**




#### **Edge Bar Banding**

The process of chemically bonding Load Bars (non-load bearing) to the cross bars after trimming to size to provide a uniform appearance on all sides of a grating panel. Available on GratEX® products:






Total area including areas cut to waste (A x B).






#### **Penetrations**

Cut out but within the grating panel as opposed to being on the edge.




The area of panel remaining after deducting areas cut to waste [AxB]-[CxD].





The section on the leading edge of a stair tread or (top stair) loading panel to assist slip resistance and to give a clear visual indication of the edge of stair treads and




#### Load Bar




### Length of Span

Overall dimension of a panel measured parallel with load bar typically indicated by this symbol "—". In the



The overall dimension of a panel – in the case of GratEX®, this is the opposite dimension to the span, or the smaller dimension and in the case of GridEX®, this is the dimension measured at right angles to the load bars, even if greater



### **Installation Suggestions & Tools**

Installing and modifying or fabricating FRP products, and in particular grating, can be done with ease on site if needed, provided you have the right tools to do so. To assist you with ensuring you are equipped properly, we have provided the following information and guidelines.

Treadwell recommends that respiratory, eye, ear, and hand PPE be worn as a minimum whenever FRP products are being cut, drilled or modified in any form









Remember to measure twice, then cut once!





### I-Series® Kits

#### 500ml Kit

Trade Price Code: F-EXSK500-I RRP: \$56.00 + GST

- 1 x 500ml tin of I-Series® (Isophthalic) resin
- 1 x 20ml bottle of catalyst
- 1 x Small mixing cup
- 1 x brush
- 1 x Repair and Maintenance

#### 1000ml Kit

Trade Price Code: F-EXSK1000-I RRP: \$105.00 + GST

- 1 x 1000ml tin of I-Series®
- 2 x 20ml bottle of catalyst
- 2 x Small mixing cup
- 4 x brush (or maybe 2?)
- 1 x Repair and Maintenance

#### V-Series® Kits

#### 500ml Kit Trade Price Code: F-EXSK500-V


RRP: \$68.00 + GST


- 1 x 500ml tin of V-Series® (Vinylester) resin
- 1 x 20ml bottle of catalyst
- 1 x Small mixing cup
- 1 x brush
- 1 x Repair and Maintenance

#### 1000ml Kit

Trade Price Code: F-EXSK1000-V RRP: \$126.00 + GST

- 1 x 1000ml tin of V-Series® (Vinylester) resin
- 2 x 20ml bottle of catalyst
- 2 x Small mixing cup
- 4 x brush (or maybe 2?)
- 1 x Repair and Maintenance

















### **Drafting Information & Manufacturing Tolerances**




### Save on detailed drafting

When providing Treadwell with grating drawings, please ensure that only the outline of the actual grating is supplied along with all penetrations and cut-outs are displayed.

Treadwell will recommend the most economical breakdown of panels to suit your floor layout — this is because our forte in FRP products means that we stock more standard size panels. Save yourself the cost and let us take the pain out of it for you.


Treadwell utilises up to date CAD technology to create panel details and erection marking plans. Further, we can then have these drawings sent via email, fax, post or courier to any location for speedy approval or mark-up — a service many of our clients agree saves a lot of time and hassle!





Panels	Size (mm)	Length (mm)	Width (mm)	Thickness (mm)
Width	920 X 3055	± 3	± 3	± 1.5
Thickness — Length	1220 X 3660 or larger	± L / 1000	±3	± 1.5
Stairtreads	Size (mm)	Width (mm)	Depth (mm)	Thickness (mm)
Width Thickness	All sizes	± 3	± 3	± 1.5


### **Embedment Angle**



The Treadwell ArchitEX™ FRP Embedment Angle provides a very sturdy base for bearing bars and has a built-in continuous angle that locks into concrete, eliminating the need for individual anchors. The FRP embedment angle is engineered using a surfacing veil and fire retardant vinylester resin system.

This unique combination produces superior strength, stiffness, wear protection and long-term corrosion resistance required for longevity in industrial applications. The FRP embedment angle is suitable for use with both GratEX®, MoultrEX® and GridEX® products and is typically available in grey 3 m or 6 m lengths.

Profile	Code	Depth	Width	Weight
25 mm	F-[E]P-EA25	25 mm	38 mm	1.34 kg/m
38 mm	F-[E]P-EA38	38 mm	38 mm	1.52 kg/m
50 mm	F-[E]P-EA50	50 mm	38 mm	1.64 kg/m
100 mm	F-[E]P-EA100	100 mm	100 mm	2.71 kg/m




### **Safety Ramp**



Treadwell's lightweight safety ramps can be adapted to any application. Flexible and sturdy enough to take even the heaviest of weights, they are resistant to fire, chemicals and corrosion. Being anti-slip in nature, FRP safety ramps are an extremely safe surface for your ramps in all types of weather.

Efficient and cost effective alternative to stainless or galvanised steel angles, these safety ramps can be readily installed onto domestic walkways, providing effective both pedestrian and wheel access.

Profile	Code	Depth	Width
25 mm	F-MG25(38/38)S-IYG*-RMP	120 mm	3660 mm
32 mm	F-MG32(38/38)S-IYG*-RMP	120 mm	3660 mm
38mm	F-MG38(38/38)S-IYG*-RMP	120 mm	3660 mm
50 mm	F-MG50(38/38)S-IYG*-RMP	158 mm	3660 mm



<sup>\*</sup>Please note that the resin composition and colouration are customisable according to specifications. Please speak to us about the many options available to suit your needs.

### StormChief®

### **StormChief**®

Treadwell developed the StormChief® fastening system to provide a solution for fastening down grating products in environments that experience high wave action and subsequently require a fastening system that is designed to withstand wave zone loadings.

Wave action exerts extreme forces on grating, sometimes causing panels to be wrenched off substructures. This damage affects large industrial offshore structures such as oil and gas drilling platforms, dockside walkways or decks, and marine based recreational public infrastructure.


StormChief® Wave Zone Grating Fasteners save organisations large expenses in downtime due to access complications and restrictions and reinstallation costs. Additionally, the systems provide time saving installation methods such as the StormChief® Hybrid System which eliminates the necessity for access to the underside of the substructure.



#### StormChief DISC®



#### Plan View




**Elevation View** 

The StormChief DISC® is an extremely robust and secure grating fastening system intended for use in areas that experience high wave zone loadings. The DISC is designed to be used when the width of a walkway or deck area exceeds 1200mm or requires securing in situations where the application of the CLAW system is impractical. The DISC is recessed to ensure safe and secure pathway for all types of traffic accessing the area. This system is compatible with the H-Clip fastener and the StormChief® Hybrid System.


#### StormChief®






**Elevation View** 

Plan View



The StormChief CLAW® is a heavy duty 316 Stainless Steel grating fixing bracket that is designed to meet and exceed specifications for wave zone loadings. With integrated fingers that protrude into the grating aperture, the StormChief CLAW® provides secure fastening in even the harshest of coastal conditions. Used exclusively in conjunction with the StormChief® Hybrid System, it ensures simple, strong and rapid installation.





**Elevation View** 

Plan View



The StormChief CLAMP® is a rugged stainless steel clamping bracket that is designed to meet and exceed the requirements of extreme wave zone loadings. The StormChief CLAMP® is a unique clamping system designed by Treadwell to seamlessly join two sheets of grating along one edge. This clip is easily recessed into the grating to ensure minimal trip hazard, making it ideal for public access areas that are subject to harsh coastal conditions.

#### StormChief® H-Clip Combination








### **Access Hatches, Handles & Hinge Systems**

#### **Access Hatches, Handles & Hinge Systems**

Treadwell can custom design any type of cover or hatch using GratEX® Solid Surface Mesh and can simply and effectively make these lockable, removable and even hinged through the use of standard and custom ancillary products such as handles, hinges, frames and cam locks.

If you should have a unique application, please don't hesitate to contact us — there is a good chance we've encountered something similar in the past.



### **Elevated Support Systems**

#### **GratEX® Adjustable FRP Elevated Floor System**



GratEX® Adjustable FRP Elevated Floor System

Code MG-AEFS
UOM Unit/Each

This adjustable pedestal, constructed completely from FRP, is designed specifically for GratEX®. It provides excellent support for elevated flooring and has a long-standing history of outstanding performance in corrosive applications. Pedestals are available in polyester and vinylester resin systems. Standard colours are grey and black.

#### **GratEX® FRP Elevated Floor System**



GratEX® FRP Elevated Floor System

Code MG-EFS
UOM Unit/Each

This fixed pedestal, also constructed from FRP, is designed for the support of elevated walkways and access-ways in dosing rooms and other areas where items on floors make access difficult. Pedestals are available in polyester and vinylester resin systems. Standard colours are grey and yellow.

#### Colossus

This unique range of non-metallic adjustable crew-jack elevated flooring pedestals offer uninterrupted adjustability and can support loads of more than 1,000 kg per pedestal. They can be adjusted to compensate up to 5% pitch, or compensate for locally uneven sub-bases up to the same amount. Once pedestals are at the required height (uninterruptedly adjustable between 17mm – 1070mm), their position is fixed with unique lockable keys.

## INCREDIBLE SLOPE CORRECTION (UP TO 5%!)

Designed to adapt to any environment, the incredibly flexible slope correction feature, which is integrated on the heads of larger pedestals and supplied separately for the smaller ones, makes for extremely simplistic and quick installation of false floors.

#### **UNIQUE HEIGHT LOCKING SYSTEM**

Specifically developed to lock the pedestal at the required height, this feature ensures no subsequent rotational movement caused by traffic or vibration will destroy the integrity of your false floor over time.

#### PITCH ALTERATION BAND

This unique feature which is 115mm in diameter allows for the screw pitch of thepedestal to be reversed if required, making your job of levelling a false floor installation a cinch!



#### **EXCELLENT SURFACE SUPPORT**

With a surface area of 175cm² and a diameter of 150mm, the head of the pedestal is screwed directly onto the base, or on to the coupler. And, what's more, the head, with a diameter of 150mm, can be fitted with various components to support different surfaces.

#### **EXTENSION COUPLERS AVAILABLE**

Couplers are able to be used whenever the height of the pedestal exceeds 175mm. Two integrated tabs on either side allow for mechanical fixing or cross bracing, guaranteeing enhanced stability when the height exceeds 600mm.


#### **STOUT & STURDY BASE**

The base can be simply positioned or fixed to any substrate. It has fixing holes for screw or bolts. The head, couplers and bases have safety 'stop' pins to prevent over extension. The base has a surface area of 314 cm<sup>2</sup> and a diameter of 200mm

### **Elevated Support Systems**



### **Appendix 1; Load Data Tables**



- The following tables were developed in accordance with the test method developed by the Fibreglass Grating Manufacturers Council (FGMC) of the American Composites Manufacturers Association(ACMA) for the Fibreglass Grating Standard.
- The designer should not exceed MAXIMUM RECOMMENDED load at any time. MAXIMUM LOAD represents factors of safety are different for moulded and pultruded grating (moulded - 5:1, pultruded - 2:1) for ULTIMATE CAPACITY. ULTIMATE CAPACITY represents MAX LOAD observed at initial fracture.
- 3. Walking loads for maintenance traffic are typically a live load of 2.87 kN/m². Deflections for worker comfort are typically limited to 9.525mm or SPAN divided by 120 under full live load. For a firmer feel under full live load or a line load 372kg/m to width, limit deflections to 6.35mm or SPAN divided by 200.
- 4. The loads represented are for STATIC LOAD CONDITIONS at ambient temperature. Deflections for impact loads or dynamic loads will MULTIPLY the deflections shown by 2. Long term loads will result in added deflection due to creep in the material and will require higher factors of safety to ensure acceptable performance.
- 5. Deflections are limited to 12.7mm as recommended by the Fibreglass Grating Manufacturers Council of the American Composites Manufacturers Association.

### **Appendix 2; Chemical Resistance Guide**

Information contained in this guide is based on data collected from several years of actual industrial applications. Recommendations are based on conservative evaluations of the changes which occur in certain properties of replicate laminates after exposures of one year or longer, both in the laboratory and the field.

Temperatures are neither the minimum nor the maximum but represent standard test conditions (Room Temperature & 70°C). The products may be suitable at higher temperatures but individual

test data should be required to establish such suitability. Contact Treadwell for any special applications that you may have.

The recommendations (• : resistant: -:not resistant) contained in this specification sheet are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory or actual field trial prior to use. Our responsibility for claims arising from breach of warranty, negligence, or otherwise is limited to the purchase price of the material.

	I-Se	ries®	V-Series®	
Chemical	Room Temp	70°C	Room Temp	70°C
Acetaldehyde	_	_	_	-
Acetic Acid 0-25%	•	•	•	•
Acetic Acid 25-50%	•	_	•	•
Acetic Anhydride	_	_	_	_
Acetone	_	_	_	_
Acrylonitrile	_	_	_	_
Alcohol, Butyl	_	_	•	_
Alcohol, Ethyl 10%	_	_	•	66
Alcohol, Ethyl 100%	_	_	•	_
Alcohol, Isopropyl 10%	_	-	•	66
Alcohol, Isopropyl 100%	_	_	•	_
Alcohol, Methyl 10%	_	_	•	66
Alcohol, Methyl 100%	_	_	_	_
Alcohol, Methyl Isobutyl	_	_	•	66
Alcohol, Secondary Butyl	_	_	•	66
Aluminium	•	•	•	•
Aluminium Chloride	•	•	•	•
Aluminium Hydroxide	•	_	•	49
Aluminium Nitrate	•	•	•	•

	I-Ser	ies®	V-Series®	
Chemical	Room Temp	70°C	Room Temp	70°C
Aluminium Potassium Sulfate	•	•	•	•
Ammonia, Aqueous 0-10%	_	_	•	38
Ammonia, Gas	_	_	•	38
Ammonium Bicarbonate	•	_	•	49
Ammonium Bisulfite	_	_	•	49
Ammonium Carbonate	_	_	•	49
Ammonium Citrate	•	_	•	49
Ammonium Fluoride	_	_	•	49
Ammonium Hydroxide 5%	•	_	•	49
Ammonium Hydroxide 10%	•	_	•	49
Ammonium Hydroxide 20%	_	_	•	49
Ammonium Nitrate	•	•	•	49
Ammonium Persulfate	_	_	•	49
Ammonium Phosphate	_	_	•	49
Ammonium Sulfate	•	•	•	•
Arsenious Sulfate	•	_	•	•
O-Benzoyl Benzoic Acid	_	_	•	•
Barium Carbonate	•	_	•	•
Barium Chloride	•	_	•	•



	I-Ser	ies®	V-Series®	
Chemical	Room Temp	70°C	Room Temp	70°C
Barium Hydroxide	_	_	•	49
Barium Sulfate	•	•	•	•
Barium Sulfide	_	_	•	•
Beer	•	_	•	49
Benzene	_	_	_	_
5% Benzene in Kerosene	•	_	•	•
Benzene Sulfonic Acid	•	•	•	•
Benzoic Acid	•	_	•	•
Benzyl Alcohol	_	_	•	_
Benzyl Chloride	_	_	_	_
Brass Plating Solution:				
– 3% Copper Cyanide	_	_	•	•
– 6% Sodium Cyanide	_	_	•	•
– 1% Zinc Cyanide	_	_	•	•
– 3% Sodium Carbonate	_	_	•	•
Butyl Acetate	_	_	_	_
Butyric Acid 0-50%	•	_	•	•
Butylene Glycol	•	•	•	•
Cadmium Chloride	•	_	•	•
Cadmium Cyanide Plating Soln:				
– 3% Cadmium Oxide	_	-	•	49
– 6% Sodium Cyanide	_	_	•	49
– 1% Caustic Soda	_	_	•	49
Calcium Bisulfate	•	•	•	•
Calcium Carbonate	•	_	•	•
Calcium Chlorate	•	•	•	•
Calcium Chloride	•	•	•	•
Calcium Hydroxide	•	-	•	49
Calcium Hypochlorite	•	_	•	49
Calcium Nitrate	•	•	•	•
Calcium Sulfate	•	•	•	•
Calcium Sulfite	•	•	•	•
Caprylic Acid	•	_	•	•
Carbon Dioxide	•	•	•	•
Carbon Disulfide	_	_	_	_
Carbon Monoxide	•	•	•	•
Carbon Tetrachloride	_	_	•	38
Carbon Acid	•	_	•	•
Castor Oil	•	•	•	•
Carbon Methyl Cellulose	_	_	•	49
Chlorinated Wax	_	_	•	•
Chlorine Doixide/Air	•	_	•	•
Chlorine Dioxide, Wet Gas	_	_	•	•
Chlorine, Dry Gas	_	_	•	•
Chlorine, Wet Gas	_	_	•	•
Chlorine, Liquid	•-	•-	•-	•-

	I-Sei	ries®	V-Series®	
Chemical	Room Temp	70°C	Room Temp	70°C
Chlorine, Water	_	_	•	•
Chloroacetic Acid 0-50%	_	_	•	38
Chlorobenzene	_	_	_	_
Chloroform	_	_	_	_
Chlorosulfonic Acid	_	_	_	_
Chromic Acid 20%	_	_	•	49
Chromic Acid 30%	_	_	_	_
Chromium Sulfate	•	•	•	•
Citric Acid	•	•	•	•
Coconut Oil	•	_	•	•
Copper Chloride	•	•	•	•
Copper Cyanide	_	-	•	•
Copper Fluoride	_	_	•	•
Copper Nitrate	•	•	•	•
Copper Plating Solution:				
- Copper Cyanide	_	_	•	•
– 10.5% Copper	_	_	•	•
– 4% Copper Cyanide	_	_	•	•
– 6% Rochelle Salts	_	_	•	•
Copper Brite Plating:				20
- Caustic Cyanide	_	_	•	38
Copper Plating Solution:				
- 45% Copper Fluorobrate	_	_	•	•
<ul><li>– 19% Copper Sulfate</li><li>– 8% Sulfuric Acid</li></ul>	_	_	•	•
	_	_	•	•
Copper Matte Dipping Bath:  – 30% Ferric Chloride	_	_		
– 19% Hydrochloric	_	_		
Copper Pickling Bath:				
– 10% Ferric Sulfate	_	_		
– 10% Sulfuric Acid	_	_	•	•
Copper Sulfate	•	•	•	•
Corn Oil	•	_	•	•
Corn Starch-Slurry	•	_	•	•
Corn Sugar	•	_	•	•
Cottonseed Oil	•	_	•	•
Crude Oil, Sour	•	_	•	•
Crude Oil, Sweet	•	_	•	•
Cyclohexane	•	_	•	49
Detergents, Sulfonated	•	_	•	•
Di-Ammonium Phosphate	•	_	•	•
Dibromophenol	_	_	_	_
Dibutyl Ether	-	_	•	49
Dichloro Benzene	_	_	_	_
Dichloroethylene	_	_	_	_
Diesel Fuel	••		••	••

Ch	I-Sei	ies®	V-Se	ries®		
Chemical	Room Temp	70°C	Room Temp	70°C	Chemical	
Diethylene Glycol	•	-	•	•	Hydrobromic Acid 0-25%	
Dimenthyl Phthalate	-	_	•	•	Hydrochloric Acid 0-37%	
Dioctyl Phthalate	_	_	•	•	Hydrocyanic Acid	
Diprophylene Gylcol	•	_	•	•	Hydrofluoric Acid 10%	
Dodecyl Alcohol	_	_	•	•	Hydrofluosilicic Acid, 10%	
Esters, Fatty Acids	•	•	•	•	Hydrogen Bromide, Wet Gas	
Ethyl Acetate	_	_	_	_	Hydrogen Chloride, Dry Gas	
Ethyl Benzene	_	_	_	_	Hydrogen Chloride, Wet Gas	
Ethyl Ether	_	_	_	_	Hydrogen Peroxide	
Ethylene Gylcol	•	•	•	•	Hydrogen Sulfide, Dry	
Ethylene Dichloride	_	_	_	_	Hydrogen Sulfide, Aqueous	
Fatty Acids		•	•	•	Hydrogen Fluoride, Vapour	
Ferric Chloride		•	•	•	Hydrosulfite Bleach	
Ferric Nitrate		•	•	•	Hydrochlorus Acid 0-10%	
Ferric Sulfate	•	•	•	•	Iron Plating Solution:	
Ferrous Chloride	•	•	•	•	– 45% Fecl: 15% Cacl	
Ferrous Nitrate	•	•	•	•	- 20% Fecl: 11% (Nh4)2 So4	
Ferrous Sulfate		•	•	•	Iron And Steel Claeaning Bath:	
8-8-8 Fertiliser		_	•	49	–9% Hydrochloric: 23% Sulfuric	
Fertiliser:				72	Isopropyl Amine	
– Urea Ammoium Nitrate	_	_		49	Isopropyl Palmitate	
Fuel Gas	_	_	•	•	Jet Fuel	
Fluoboric Acid	_	_		49	Kerosene	
Fluosilicic Acid 0-20%	_	_		•	Lactic Acid	
Formaldehyde		_		•	Lauroryl Chloride	
Formic Acid		_			Lauric Acid	
Fuel Oil		_			Lead Acetate	
Gas Natural		_	•		Lead Chloride	
Gasoline, Auto					Lead Nitrate	
Gasoline, Aviation			•		Lead Plating Solution:	
Gasoline, Ethyl		_	•	•	8% Fluoboric, 0.4% Boric Acid	
Gluconic Acid	•	_	•	•	Levulinic Acid	
Gasoline, Sour		_	•	•	Linseed Oil	
Glucose		_	•	•	Lithium Bromide	
		•	•	•	Lithium Sulfate	
Glycerine	•	•	•	•	Magnesium Bisulfite	
Glycol, Ethylene	•	•	•	•		
Glycol, Propylene	•	•	•	•	Magnesium Carbonate  Magnesium Chloride	
Glycolic Acid	•	_	•	•		
Gold Plating Solution:					Magnesium Hydroxide	
- 63% Potassium Ferrocyanide	_	_	•	•	Magnesium Nitrate	
– 2% Potassium Gold Cyanide	_	_	•	•	Magnesium Sulfate	
– 8% Sodium Cyanide	_	_	•	•	Maleic Acid	
Heptane	•	_	•	•	Mercuric Chloride	
Hexane Hexylene Glycol	•	_	•	•	Mercurous Chloride  Methylene Chloride	

	I-Series®		V-Series®		
Chemical	Room Temp	70°C	Room Temp	70°C	
Hydrobromic Acid 0-25%	•	_	•	•	
Hydrochloric Acid 0-37%	•	_	•	•	
Hydrocyanic Acid	•	_	•	•	
Hydrofluoric Acid 10%	_	_	•	_	
Hydrofluosilicic Acid, 10%	_	_	•	•	
Hydrogen Bromide, Wet Gas	_	_	•	•	
Hydrogen Chloride, Dry Gas	_	_	•	•	
Hydrogen Chloride, Wet Gas	_	_	•	•	
Hydrogen Peroxide	_	_	•	49	
Hydrogen Sulfide, Dry	•	_	•	•	
Hydrogen Sulfide, Aqueous	•	_	_	•	
Hydrogen Fluoride, Vapour	_	_	•	•	
Hydrosulfite Bleach	_	_	•	49	
Hydrochlorus Acid 0-10%	_	_	_	_	
Iron Plating Solution:					
– 45% Fecl: 15% Cacl	_	_	•	•	
– 20% Fecl: 11% (Nh4)2 So4	_	_	•	•	
Iron And Steel Claeaning Bath:					
−9% Hydrochloric: 23% Sulfuric	_	_	•	•	
Isopropyl Amine	_	_	•	38	
Isopropyl Palmitate	•	•	•	•	
Jet Fuel	•	_	•	•	
Kerosene	•	_	•	•	
Lactic Acid	•	_	•	•	
Lauroryl Chloride	_	_	•	•	
Lauric Acid	•	_	•	•	
Lead Acetate	•	_	•	•	
Lead Chloride	•	_	•	•	
Lead Nitrate	•	_	•	•	
Lead Plating Solution:					
8% Fluoboric, 0.4% Boric Acid	_	_	•	•	
Levulinic Acid	•	_	•	•	
Linseed Oil	•	•	•	•	
Lithium Bromide	•	•	•	•	
Lithium Sulfate	•	•	•	•	
Magnesium Bisulfite	•	-	•	•	
Magnesium Carbonate	•	_	•	•	
Magnesium Chloride	•	•	•	•	
Magnesium Hydroxide	_	_	•	60	
Magnesium Nitrate	•	_	•	•	
Magnesium Sulfate	•	•	•	•	
Maleic Acid	•	•	•	•	
Mercuric Chloride	•	_	•	•	
Mercurous Chloride	•	_	•	•	
Methylene Chloride	_	_	_	_	
Methyl Ethyl Ketone	_	_	_	_	



	I-Sei	ries®	V-Series®	
Chemical	Room Temp	70°C	Room Temp	70°C
Methyl Isobutyl Carbitol	_	_	_	_
Methanol (See Alcohol)	•	_	•	•
Methyl Isobutyl Ketone	_	_	_	_
Methyl Styrene	_	_	_	_
Mineral Oils	•	•	•	•
Molybdenum Disulfide	•	_	•	•
Monochloro Acetic Acid	-	_	_	_
Monoethyanolamine	-	_	_	_
Motor Oil	•	•	•	•
Myristic Acid	_	_	•	•
Naptha	•	•	•	•
Napthalene	•	_	•	•
Nickel Chloride	•	•	•	•
Nickel Nitrate	•	•	•	•
Nickel Plating:				
- 8% Lead, 0.8% Flouboric Acid	-	_	•	•
- 0.4% Boric Acid	_	_	•	•
Nickel Plating:				
<ul> <li>11% Nickel Sulfate</li> </ul>	•	_	•	•
- 2% Nickel Chloride	•	_	•	•
- 1% Boric Acid	•	_	•	•
Nickel Plating:				
- 44% Nickel Sulfate	•	_	•	•
<ul> <li>4% Ammonium Chloride</li> </ul>	•	_	•	•
- 4% Boric Acid	•	_	•	•
Nickel Sulfate	•	•	•	•
Nitric Acid 0-5%	•	•	•	•
Nitric Acid 20%	_	_	•	49
Nitric Acid Fumes	_	_	_	_
Nibrobenzene	-	_	_	_
Octanoci Acid	•	-	•	•
Oil, Sour Crude	•	•	•	•
Oil, Sweet Crude	•	•	•	•
Oleic Acid	•	•	•	•
Oleum (Fuming Sulfuric)	-	_	-	-
Olive Oil	•	•	•	•
Oxalic Acid	•	•	•	•
Peroxide Bleach:				
– 25% Peroxide 95%	•	•	•	•
- 0.025% Epsom Salts	•	•	•	•
- 5% Sodium Silicate 42.Be	•	•	•	•
- 1.4% Sulfuric Acid 66.Be	•	•	•	•
Phenol	_	_	_	_
Phenol Sulfonic Acid	_	_	_	_
Phosphoric Acid	•	•	•	•
Phosphoric Acid Fumes	•	•	•	•

	I-Ser	ries®	V-Series®	
Chemical	Room Temp	70°C	Room Temp	70°C
Phosphorous Pentoxide	•	•	•	•
Phosphorous Trichloride	_	_	_	_
Phthalic Acid	•	•	•	•
Pickling Acids (Sulfuric & Hydrochloric)	•	•	•	•
Picric Acid, Alcoholic	_	_	_	_
Polyvinyl Acetate Latex	•	_	•	•
Polyvinyl Alcohol	•	_	•	38
Polyvinyl Chloride Latex W/35 (Parts Dop)	-	-	•	49
Potassium Aluminium Sulfate	•	•	•	•
Potassium Bicarbonate	•	_	•	60
Potassium Bromide	•	_	•	38
Potassium Carbonate	•	_	•	60
Potassium Chloride	•	•	•	•
Potassium Dichromate	•	_	•	60
Potassium Ferricyanide	•	•	•	•
Potassium Ferrocyanide	•	•	•	•
Potassium Hydroxide	_	_	•	66
Potassium Nitrate	•	•	•	•
Potassium Permanganate	•	_	•	60
Potassium Persulfate	•	_	•	•
Potassium Sulfate	•	•	•	•
Propionic Acid 1-50%	-	_	•	49
Propionic Acid 50-100%	_	_	_	_
Propylene Glycol	•	•	•	•
Pulp Paper Mill Effluent	•	_	•	•
Pyridine	_	_	-	_
Salicylic Acid	_	_	•	60
Sebacic Acid	_	_	•	•
Selenious Acid	_	_	•	•
Silver Nitrate	•	•	•	•
Silver Plating Solution:				
- 44% Silver Cyanide	-	_	•	•
– 7% Potassium Cyanide	-	-	•	•
- 5% Sodium Cyanide	-	_	•	•
<ul> <li>2% Potassium Carbonate</li> </ul>	-	-	•	•
Soaps	•	_	•	•
Sodium Acetate	•	-	•	•
Sodium Benzoate	•	_	•	•
Sodium Bicarbonate	•	•	•	•
Sodium Bifluoride	•	_	•	49
Sodium Bisulfate	•	•	•	•
Sodium Bisulfite	•	•	•	•
Sodium Bromate	•	•	•	60
Sodium Bromide	•	•	•	•
Sodium Carbonate 0-25%	•	_	•	•

	I-Sei	ries®	V-Series®	
Chemical	Room Temp	70°C	Room Temp	70°C
Sodium Chlorate	•	_	•	•
Sodium Chloride	•	•	•	•
Sodium Chlorite	•	_	•	•
Sodium Chromite	•	•	•	•
Sodium Cyanide	•	_	•	•
Sodium Dichromate	•	•	•	•
Sodium Di-Phosphate	•	•	•	•
Sodium Ferricyanide	•	•	•	•
Sodium Fluoride	•	_	•	49
Sodium Fluoro Silicate	_	_	•	49
Sodium Hexametaphosphates	_	_	•	38
Sodium Hydroxide 0-5%	_	_	•	66
Sodium Hydroxide 5-25%	_	_	•	66
Sodium Hydroxide 50%	_	_	•	66
Sodium Hydrosulfide	•	_	•	•
Sodium Hypochlorite	•	_	•	66
Sodium Lauryl Sulfate	•	•	•	•
Sodium Mono-Phosphate	•	•	•	•
Sodium Nitrate	•	•	•	•
Sodium Silicate	•	_	•	•
Sodium Sulfate	•	•	•	•
Sodium Sulfide	•	_	•	•
Sodium Sulfite	•	_	•	•
Sodium Tetra Borate	•	•	•	•
Sodium Thiocyanate	_	_	•	•
Sodium Thiosulfate	•	_	•	•
Sodium Tripolyphosphate	•	_	•	•
Sodium Xylene Sulfonate	•	_	•	•
Sodium Solutions	•	_	•	•
Sodium Crude Oil	•	•	•	•
Soya Oil	•	•	•	•
Stannic Chloride	•	•	•	•
Stannous Chloride	•	•	•	•
Stearic Acid	•	•	•	•
Styrene	_	_	_	_
Sugar, Beet And Cane Liquor	•	_	•	•
Sugar, Sucrose	•	•	•	•
Sulfamic Acid	•	-	•	•
Sulfanilic Acid	•	_	•	•
Sulfated Detergents	•	_	•	•
Sulfur Dioxide, Dry Or Wet	_	_	•	•
Sulfur Trioxide/Air	_	_	•	•
Sulfuric Acid 0-30%	•	•	•	•
Sulfuric Acid 30-50%	_	_	•	•
Sulfuric Acid 50-70%	_	_	•	49
Sulfurous Acid	_	_	•	38

	I-Sei	ries®	V-Series®	
Chemical	Room Temp	70°C	Room Temp	70°C
Superphosphoric Acid (76% P2 05)	•	_	•	•
Tall Oil	•	_	•	60
Tannic Acid	•	_	•	66
Tartaric Acid	•	•	•	•
Thionyl Chloride	_	_	_	_
Tin Plating:				
– 18% Stannous Fluorborate	-	_	•	•
– 7% Tin	_	_	•	•
– 9% Fluoroboric Acid	-	_	•	•
– 2% Boric Acid	-	-	•	•
Toluene	_	_	_	_
Toluene Sulfonic Acid	_	_	•	•
Transformer Oils:				
– Mineral Oil Types	•	•	•	•
– Chloro-Phenyl Types)	•	•	•	•
Trichlor Acetic Acid	•	-	•	•
Trichlorethylene	_	_	_	_
Trichloropenol	-	-	_	_
Tricresyl Phosphate	_	_	•	49
Tridecylbenzene Sulfonate	•	-	•	•
Trisodium Phosphate	•	_	•	•
Turpentine	-	_	•	38
Urea	_	_	•	38
Vegetable Oils	•	•	•	•
Vinegar	•	•	•	•
Vinyl Acetate	_	_	_	_
Water:				
– Deionised	_	_	_	_
– Demineralised	•	•	•	•
– Distilled	•	•	•	•
– Fresh	•	•	•	•
– Salt	•	•	•	•
- Sea	•	•	•	•
White Liquor (Pulp Mill)  Xylene	•	_	•	•
Zinc Chlorate	_	_	_	_
Zinc Nitrate				
Zinc Nitrate  Zinc Plating Solution:	•	•	•	•
<ul><li>– 9% Zinc Cyanide</li></ul>	_	_		49
– 4% Sodium Cyanide	_	_		49
– 4 % Sodium Cyamide	_	_		49
Zinc Plating Solution:				47
- (49% Zinc Fluoroborate	•	_	•	•
- 5% Ammonium Chloride	•	_	•	•
– 6% Ammonium Fluoroborate	•	_	•	•
Zinc Sulfate	•	•	•	•
0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0				



## Appendix 3: GratEX® Ordering Codes

		F-MG380	(38/38)S-IGG/1			
Code		De	escription			
F-MG		Fibreglass Moul	ded Grating - Grat	EX®		
			sh Thickness			
	13	15mm	30	30mm		
	14	20mm	35	35mm		
			38	38mm		
38	15	22mm	50	50mm		
	20	23mm	53	53mm		
	22	25mm	55	55mm		
	23		60	60mm		
	25		63	63mm		
		Ν	lesh Aperture			
	(13/13) = 13mm x 13m	nm	(38/38) = 3	38mm x 38mm		
	(14/14) = 14mm x 14m			= 38mm x 100mm		
	(19/19) = 19mm x 19m		` ' '	: 38mm x 152mm		
(38/38)	(20/20) = 20mm x 20r		-	40mm x 40mm		
	(25/25) = 25mm x 25n		(50/50) = 50mm x 50mm			
_	(25/50) = 25 mm x  50 n		(60/220) = 60mm x 220mm			
		(25/100) = 25mm x 100mm		79mm x 79mm		
	(25/152) = 25mm x 15			83mm x 83mm		
		Λ	lesh Detail			
	<b>S</b> Standard Square			cro Mesh		
S	<b>DS</b> Diagonal Square			R Rectangular Mesh  HDR Heavy Duty Rectangular Mesh		
			(3)F Solid Surface (3mm Flat) Mesh			
	<b>HDS</b> Heavy duty Squar	e Mesn	(5)F Solid Surface (5mm Flat) Mesi			
	M Mini Mesh			avy Duty Solid Surface (Flat) Mesh		
			esin Type			
			- O-Series®			
'			- I-Series®			
		V =	- V-Series®			
	G = Industrial Green		Colour DG = Dark	Grev		
G	Y = Safety Yellow		DG = Dark Grey  CH = Charcoal			
	LG = Light Grey		C = Custon			
	20 2.3.11 0.09	Suri	ace Option			
G	CG = Commercial Grad		<u> </u>	ne Grade (Grit) Anti-Slip		
_	G = Industrial Grade (G	· · · · · · · · · · · · · · · · · · ·	CH = Cheq			
	d – Illuustilat Glade (G	<u> </u>	P = Plain ( anel Size	Flat)		
			5mm x 3665mm			
	2 = 920mm x 3055mm					
		3 =	= Custom*			
1		Panel Si	ze (Mini Mesh)			
			'mm x 3687mm.			
		2 = 1527	'mm x 3007mm.			
	2 = 1527mm x 3007mm.  Note: This section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a					

## Appendix 4: MoultrEX® Ordering Codes

		F-MPG38(38/100)R-IGG/1	
Code		Description	
F-MPG		Fibreglass Moultruded Grating - MoultrEX®	
		Mesh Thickness	
38	38	38mm	
	50	50mm	
		Mesh Aperture	
(38/100)		$(25/100) = 25 \text{mm} \times 100 \text{mm}$	
		(38/100) = 38mm x $100$ mm	
R		Mesh Detail	
TX.		R Rectangular Mesh	
		Resin Type	
ı		O = O-Series®	
·		I = I-Series®	
		V = V-Series®	
		Colour	
		G = Industrial Green	
		Y = Safety Yellow	
G		LG = Light Grey	
	DG = Dark Grey		
		CH = Charcoal	
		C = Custom	
		Surface Option	
		CG = Commercial Grade (Grit) Anti-Slip	
		G = Industrial Grade (Grit) Anti-Slip	
G		MG = Marine Grade (Grit) Anti-Slip	
		CH = Chequer Plate	
		P = Plain (Flat)	
		Panel Size	
		1 = 1225mm x 3665mm	
1		2 = 920mm x 3055mm	
		3 = Custom*	
		oding is separated by a slash (/), it isn't required for custom jobs as GratEX® is size panels to suit applications .	



# **Appendix 5: GridEX® Ordering Codes**

		F-PG38(15/1	5)B-VGG/1			
Code	Description					
F-PG	Fibreglass Pultruded Grating - GridEX®					
38	Mesh Thickness					
	25	25mm	52	52mm		
	39		- 67 80	67mm 80mm		
		Mesh	Aperture	Comm		
	(5.3/7.8) = 5.3mm x 7.8mm (15/22.8) = 15mm x 22.8mm					
	(7.8/5	.3) = 7.8mm x 5.3mm	(15/23) = 15mm x 23mm			
(15/15)		8) = 7.8mm x 7.8mm	(22/25) = 22mm x 25mm			
. , ,			(25/5) = 22mm x 5mm			
		2) = 7.8mm x 12mm	(25	5/12.7) = 25mm x 12.7mm		
		0) = 15mm x 10mm	(40/9.6) = 40mm x 9.6mm			
	(15/1	5) = 15mm x 15mm		0/22.3) = 40mm x 22.3mm		
		Mes	sh Detail			
В	<b>I</b> l Type					
О	<b>T</b> T Type					
	<b>B</b> B Type					
		Resin Type				
V	O = O-Series®					
V	I = I-Series®					
	V = V-Series®					
	Colour					
G	G = Industrial Green		DG = Dark Grey			
	Υ =	= Safety Yellow	CH = Charcoal			
	LG	= Light Grey	C = Custom			
	Surface Option					
	CG - Com	CG = Commercial Grade (Grit) Anti-Slip		MG = Marine Grade (Grit) Anti-Slip		
G	Cd – Collin			CH = Chequer Plate		
	G = Indu	strial Grade (Grit) Anti-Slip	P = Plain (Flat)			
	Panel Size					
	1 = 1225mm x 3665mm					
1	2 = 920mm x 3055mm					
	3 = Custom*					
	Note: This section of coding is separated by a slash (/), it isn't required for custom jobs as GratEX® is available in a variety of size panels to suit applications.					
	available in a variety of size parties to suit applications.					

## Appendix 6a: GratEX® Fasteners Ordering Information

		F-MG38(38	/38)S-M316			
Code	Description					
F-MG	Fibreglass Moulded Grating - GratEX®					
	Mesh Thickness					
38	13	13mm	35	35mm		
	14	14mm	38	38mm		
	15	15mm	50	50mm		
	20	20mm	53	53mm		
	22	22mm	55	55mm		
_	23	23mm	60	60mm		
_	25	25mm	63	63mm		
_	30	30mm	~	Universal		
	Mesh Aperture					
	(13/13) = 13mm x 13mm (38/38) = 38mm x 38mm		38/38) = 38mm x 38mm			
-	(14/14) = 14mm x 14mm		(:	(38/100) = 38mm x 100mm		
	(19/19) = 19mm x 19mm			(38/152) = 38mm x 152mm		
(38/38)	(20/20) = 20mm x 20mm			(40/40) = 40mm x 40mm		
	(25/25) = 25mm x 25mm			(50/50) = 50mm x 50mm		
	(25/50) = 25mm x 50mm			(60/220) = 60mm x 220mm		
_	(25/100) = 25mm x 100mm			(79/79) = 79mm x 79mm		
				(83/83) = 83mm x 83mm		
	(25/152) = 25mm x 152mm (~) Universal					
	Mesh Detail  Standard Square  MM Micro Mesh					
S	S Standard Square					
_	<b>DS</b> Diagonal Square		HDR H			
_	HDS Heavy duty Square Mesh			Solid Surface (Flat) Mesh		
	M Mini Mesh HDF Heavy Duty Solid Surface (Flat) Mesh			eavy Duty Solid Surface (Flat) Mesh		
	M	Clip M Clip	Type	S Clip		
_	C	C Clip	S	J Clip		
_	L	L Clip	Н	H Clip		
M	D	D Clip	G	G Clip		
	E	E Clip	U	U Clip		
	W	W Clip	V	V Clip		
	0	O Clip	Т	T Clip		
	Clip Material					
316	304	304 Stainless Steel	2507	Super Duplex Stainless Steel		
	316	316 Stainless Steel	ALU	Aluminium		
	2205	Duplex Stainless Steel	HDG	Hot Dipped Galvanised		



## Appendix 6b: MoultrEX® Fasteners Ordering Information


F-MPG38(25/100)R-M316					
Code	Code Description				
F-MPG	Fibreglass Moultruded Grating - MoultrEX®				
	Mesh Thickness				
38		38	38mm		
		50	50mm		
		~	Universal		
	Mesh Aperture				
		(25/100) = 25mm	x 100mm		
(25/100)	(38/100) = 38mm x 100mm				
	(~) Universal				
	Mesh Detail				
R	<b>R</b> Rectangular Mesh				
	Clip Type				
		M	M Clip		
		J	J Clip		
M		G	G Clip		
		U	U Clip		
		V	V Clip		
	Clip Material				
316	304	304 Stainless Steel	2507	Super Duplex Stainless Steel	
	316	316 Stainless Steel	ALU	Aluminium	
	2205	Duplex Stainless Steel	HDG	Hot Dipped Galvanised	

## **Appendix 6c: GridEX® Fasteners Ordering Information**

	F-PG38(15/15)I-M316				
Code	Description				
F-PG	Fibreglass Pultruded Grating - GridEX®				
38	Mesh Thickness				
		25	25mm		
		38	39mm		
		50 50mm			
		64	64mm		
		76	76mm		
		Mesh Aperture			
	(5.3/7.	(5.3/7.8) = 5.3mm x 7.8mm		(15/23) = 15mm x 23mm	
	(7.8/5.3) = 7.8mm x 5.3mm		(22/25) = 22mm x 25mm		
	(7.8/7.8) = 7.8mm x 7.8mm		(25/5) = 22mm x 5mm		
(15/15)	(7.8/12) = 7.8mm x 12mm		(25/12.7) = 25mm x 12.7mm		
	(15/10	(15/10) = 15mm x 10mm		(40/9.6) = 40mm x 9.6mm	
	(15/15) = 15mm x 15mm		(40/22.3) = 40mm x 22.3mm		
	(15/22	(15/22.8) = 15mm x 22.8mm		(~) Universal	
	Mesh Detail				
		ı	l Type		
I		Т	T Type		
		В	B Type		
	Clip Type				
		M	M Clip		
			J Clip		
М		J G	G Clip		
		U	U Clip		
		v	V Clip		
	Clip Material				
	304	304 Stainless Steel	2507	Super Duplex Stainless Steel	
316	316	316 Stainless Steel	ALU	Aluminium	
		Duplex Stainless Steel			
	2205	Duplex Stainless Steet	HDG	Hot Dipped Galvanised	




### **Notes**




## **EX-Series**°

### Notes





### **Notes**







### TREADWELL

Treadwell Access Systems, Ex-Series®, GratEX®, GridEX®, MoultrEX® and StormChief® are all registered brands of Treadwell Group Pty Ltd. All pictures and information are supplied as a guide only. The complete range of Treadwell products are developed, refined and made to meet and exceed stringent specifications for the worldwide market.

Important Note: Sales of products are subject to our Terms and Conditions which are available upon request. All specifications and photos are a guide only and are subject to change without notice. Please ring to confirm details. Treadwell products only comply with relevant standards mentioned within this publication when installedand used as they are designed to be.



